

通过 **ISO9001:2000**
质量管理体系认证



JINTAI SLIDE BEARING

湖南锦泰五金机电有限公司

Hunan Jintai Hardware and Machinery Co., LTD



JINTAI SLIDE BEARING INTRODUCTION

COMPANY & CERTIFICATES



Hunan Jintai Hardware and Machinery Co.,Ltd is a professional manufacturer on various kind of bearings in China for over 15 years.We are making all kinds of slide bearings including DU PTFE composit bushing, DX POM composite bushing,bimetal bushing,wrapped bronze bushing, cast sliding bushings and wear plate bearing pad, sintered bronze bushing and sintering parts, graphite bearing, etc.

The shapes of bearings can be in sleeve, flanged, spherical, plate, washer, pad, ring, square, etc.

Base materials in carbon steel, harden steel, iron, stainless steel, bronze, brass, copper, bronze-steel alloy.Lubricant materials in PTFE, teflon, POM, nylon, plastic, oil, graphite, grease, MoS2,etc.



◇ SF-1



◇ SF-1F



◇ SF-WD



◇ SF-2



◇ JF-800



◇ FB090



◇ FB092



◇ FB08G



◇ FB09G



◇ JDB



◇ FZ




◇ FD

SF-1 自润滑卷制轴承 SF-1 Self-Lubricatin Bearin s



1. 聚四氟乙烯与铅 PTFE with Iead
2. 球形青铜粉 Porous bronze sintere
3. 钢背 Steel backing
4. 镀铜/锡层 Copper-plating/tin-plating



注：SF-1 系列产品还可根据不同工况条件选择不同的基体材料，如：青铜基板

（SF-1B）、不锈钢基板（SF-1S）、以及无铅（SF-1W）等配方产品。

Note: Various materials are suitable for SF-1 Series products according to different working conditions, such as bronze backing (SF-1B), stainless steel backing (SF-1S) and lead-free material (SF-1W)...

技术参数 Tech.Data

最大荷载 Max.Load	静承载 Static	250N/mm ²
	动承载 Dynamic	140N/mm ²
	摇摆运动 Oscillating	60N/mm ²
最大PV值 PV limit	干摩擦 Dry	3.6N/mm ² ·m/s
	油润滑 Oil	50N/mm ² ·m/s
使用温度 Temp.limit		-195℃~+280℃

摩擦系数 Friction Coeff.		0.03~0.20 μ
最大速率 Speed limit	干摩擦 Dry	2mm ²
	油润滑 Oil	5mm ²
导热系数 Thermal conductivity		2.41Kcal/M.br.c
热膨胀系数 Coeff. of linear expansion		27 × 10 ⁻⁶ per℃

SF-1 应用特点 Product characteristics

◎无油润滑或少油润滑，适用于无法加油或很难加油的场所，可在使用时不保养或少保养。

◎耐磨性能好，摩擦系数小，使用寿命长。

◎有适量的弹塑性，能将应力分布在较宽的接触面上，提高轴承的承载能力。

◎静动摩擦系数相近，能消除低速下的爬行，从而保证机械的工作精度。

◎能使机械减少振动、降低噪音，防止污染，改善劳动条件。

◎在运转过程中能形成转移膜，起到保护对磨轴的使用，无咬轴现象。

◎对磨轴的硬度要求低，未经调质处理的轴都可使用，从而降低了相关零件的加工难度。

◎薄壁结构、质量轻，可减小机械体积。

◎钢背面可电镀多种金属，可在腐蚀介质中使用；目前已广泛应用于各种机械的滑动部分，例如：印刷机、纺织机、烟草机械、微电机，汽车、摩托车与农林机械等等。

◎It may be used where no oil can be applied or oil is difficult to be applied.

◎It has the advantage of low wear, low friction and with long life.

Load will spread over a wider area due to the bearing material' s elastic nature.

◎Low stick slip properties ensuring accuracy of machine operation under low sliding speeds.

◎Low vibration, low noise and non-pollution in operation.

◎PTFE and Lead film is transferred to the mating shaft to improve running properties.


◎It can be used in low harness of mating shaft, so the shafts processing is easy.

◎The machine will be compact because of the thin thickness and low weight of the bush.

◎Electro plating is possible to prevent corrosion. It is widely used in various sliding motions of different kind of machines such as textile machine, tobacco machines, hydraulic vehicles Automobiles, agriculture machines and so on.

SF-1 自润滑卷制轴承标准公制尺寸

SF-1 Self-Lubricating Bearings Standard Metric Size



单位 Unit: mm

d	D	相配轴径 Shaft Dia. f ₇	座孔 Housing H7	壁厚 Wall Thickness		f ₁	f ₂	L ⁰ _{-0.40}									
				最小 Min.	最大 Max.			6	8	10	12	15	20	25	30	40	50
6	8	6 ^{-0.013} _{-0.028}	8 ^{+0.015}					0606	0608	0610							
8	10	8 ^{-0.013} _{-0.028}	10 ^{+0.015}					0806	0808	0810	0812	0815					
10	12	10 ^{-0.016} _{-0.034}	12 ^{+0.018}					1006	1008	1010	1012	1015	1020				
12	14	12 ^{-0.016} _{-0.034}	14 ^{+0.018}					1206	1208	1210	1212	1215	1220	1225			
13	15	13 ^{-0.016} _{-0.034}	15 ^{+0.018}	0.980	1.005	0.6	0.3			1310			1320				
14	16	14 ^{-0.016} _{-0.034}	16 ^{+0.018}							1410	1412	1415	1420	1425			
15	17	15 ^{-0.016} _{-0.034}	17 ^{+0.018}							1510	1512	1515	1520	1525			
16	18	16 ^{-0.016} _{-0.034}	18 ^{+0.018}							1610	1612	1615	1620	1625			
17	19	17 ^{-0.016} _{-0.034}	19 ^{+0.021}							1710	1712		1720				
18	20	18 ^{-0.016} _{-0.034}	20 ^{+0.021}							1810	1812	1815	1820	1825			
20	23	20 ^{-0.020} _{-0.041}	23 ^{+0.021}							2010	2012	2015	2020	2025	2030		
22	25	22 ^{-0.020} _{-0.041}	25 ^{+0.021}	1.475	1.505	0.6	0.4			2210	2212	2215	2220	2225	2230		
24	27	24 ^{-0.020} _{-0.041}	27 ^{+0.021}									2415	2420	2425	2430		
25	28	25 ^{-0.020} _{-0.041}	28 ^{+0.021}							2510	2512	2515	2520	2525	2530	2540	2550
28	32	28 ^{-0.020} _{-0.041}	32 ^{+0.025}									2815	2820	2825	2830	2840	
30	34	30 ^{-0.020} _{-0.041}	34 ^{+0.025}								3012	3015	3020	3025	3030	3040	
32	36	32 ^{-0.025} _{-0.050}	36 ^{+0.025}	1.970	2.005	1.2	0.4						3220		3230	3240	
35	39	35 ^{-0.025} _{-0.050}	39 ^{+0.025}								3512	3515	3520	3525	3530	3540	3550
38	42	38 ^{-0.025} _{-0.050}	42 ^{+0.025}									3815			3830	3840	
40	44	40 ^{-0.025} _{-0.050}	44 ^{+0.025}								4012		4020	4025	4030	4040	4050

注：孔径壁厚符合样本，宽度尺寸不在样本范围内客户提出要求，制造厂可定制加工。


Note: Bearing size besides above mentioned sizes, can be customized and produced. Customer please offer us the dimensions.

单位Unit: mm

[illegible]

SF-1F 自润滑卷制翻边轴承标准公制尺寸

SF-1F Self-Lubricating Flanged Bearings Standard Metric Size



单位 Unit: mm

相配轴径 Shaft Dia. f_7	座孔 Housing H7	代号 Code number	尺寸 Size					f_1	f_2
			d_1	d_2	$d_3 \pm 0.5$	$L \pm 0.25$	$\ell_1 - 0.2$		
6 ^{-0.013 -0.028}	8 ^{+0.015}	06040	6	8	12	4			
		06070				7			
8 ^{-0.013 -0.028}	10 ^{+0.015}	08055	8	10	15	5.5			
		08075				7.5			
10 ^{-0.016 -0.034}	12 ^{+0.018}	10070	10	12	18	7			
		10090				9			
		10120				12			
12 ^{-0.016 -0.034}	14 ^{+0.018}	12070	12	14	20	7			
		12090				9			
		12120				12	1	0.6	0.3
14 ^{-0.016 -0.043}	16 ^{+0.018}	14120	14	16	22	12			
		14170				17			
		15090				9			
15 ^{-0.016 -0.034}	17 ^{+0.018}	15120	15	17	23	12			
		15170				17			
		16120	16	18	24	12			
16 ^{-0.016 -0.034}	18 ^{+0.018}	16170				17			
		18120				12			
18 ^{-0.016 -0.034}	20 ^{+0.021}	18170	18	20	26	17			
		18200				20			
		20115				11.5			
20 ^{-0.020 -0.041}	23 ^{+0.021}	20165	20	23	30	16.5			
		20215				21.5			
		22150	22	25	32	15	1.5	0.6	0.4
22 ^{-0.020 -0.041}	25 ^{+0.021}	22200				20			
		25115				11.5			
25 ^{-0.020 -0.041}	28 ^{+0.021}	25165	25	28	35	16.5			
		25215				21.5			
		30160	30	34	42	16			
30 ^{-0.025 -0.050}	34 ^{+0.025}	30260				26			
		35160	35	39	47	16			
		35260				26	2	1.2	0.4
40 ^{-0.025 -0.050}	44 ^{+0.025}	40260	40	44	53	26			
		40400				40			

SF-2 边界润滑轴承 SF-2 Marginal-Lubrication Bearings




1. 改性聚甲醛 POM with lead 0.3-0.5mm
2. 球形青铜粉 Porous bronze sintere
3. 钢背 Steel backaking
4. 镀铜层 Copper plating



注：SF-2 系列产品还可根据
不同工况条件选择不同的基
体材料，如：青铜基板、不
锈钢基板、以及“无铅”等
配方产品。SF-2Y 属环保无
铅产品，颜色为桔黄色。

Note: Various materials
are suitable for SF- 2
series products
according to different
working conditions,
such as bronze-
backing, stainless steel
backing and lead-free
material. SF-2Y is an
environmental friendly
lead-free product and its
color is orange.



技术参数 Tech.Data

最大何载 Max Load	静承载 Static	250N/mm ²
	动承载 Dynamic	140N/mm ²
	摇摆运动 Oscillating	60N/mm ²
最大 PV 值 PV limit	干摩擦 Dry	2.8N/mm ² ·m/s
	润滑油 Oil	22N/mm ² ·m/s
使用温度 Temp.limit		-40℃~+130℃
摩擦系数 Friction Coeff.		0.05~0.25 μ
最大速率 Speed limit		0.25m/s
导热系数 Thermal conductivity		2.03Kcal/M.br.C
热膨胀系数 Coeff. of linear expansion		51×10 ⁻⁶ per℃
装配时内孔涂润滑油 Initial pre-lubrication at assembly required		

SF-2 应用特点 Characteristic of preformance

◎SF-2 型材料是以填充四氟改性的聚甲醛塑料为表面层三层复合自润滑材料，它是一种良性的边界润滑材料，因此特别适用与高载低速下的旋转运动，摇摆运动以及经常在载荷下启闭而不易形成流体动力润滑的轴承，止推垫片、滑块、球座等摩擦零件。SF-2 能够充分地利用微量润滑脂，在边界润滑条件下可以长期的不用加油保养。在完全无油润滑条件下，SF-2 磨擦性能及允许 PV 值较低，因此通常在塑料表面轧出储油坑，装配时涂上锂基润滑油或硅脂等。

◎SF-2 is triple-layer self lubricating material that can fill modified POM plastic as surface layer; it is benignant boundary lubrication material, therefore, it is particularly applicable high-load low-speed rotating and wing movement, as well as in the condition that frequent loaded start-stop is the requirement while hydrodynamic lubrication membrane is difficult to form, in the parts such as bearing, thrust washer, sliding block, ball socket and so on. SF-2 can take full advantage of less grease to work long time without lubrication maintenance under boundary lubrication condition. But under oil-free condition, SF-2 the frictional behavior and permissible PV value is relatively low, so generally storage pit can be formed on the plastic surface, where lithium-based lubricant grease or silicone grease and so on should be applied when being installed.

SF-2 磨损规律 Wear and tear a law

◎SF-2 型材料有其特殊的磨损规律，如图 4 所示在安装时涂油脂的情况下，能在 R 阶段内极微量的磨损。经过 R 阶段时间后失去边界油润滑条件，磨损就开始加剧。如果在此时重新加油，可保持无显著磨损，其寿命亦可以大大地延长。所以 SF-2 材料的优点就在于需要间融 R 阶段时间加油一次，其间隔时间 R 较其它材料特别是金属材料的间隔时间显著地长。约为五倍左右。

◎SF-2 material follows special wearing rule as shown in Fig. 4, infinitesimal abrasion can occur in R phase when being applied with grease and then being installed. But after the R phase, the boundary lubrication condition will disappear and wearing will be exaggerated. If you do refill with oil, the product can be drastically held by non-remarkable wearing and its life will also be greatly extended. Therefore the advantage of SF-2 material is that oil should be added with an interval of R, which is remarkably longer than that of other metal materials. It is approximately five times as long.

◎当装配时涂以润滑脂(如锂基脂或硅脂等)，SF-2 衬套的使用寿命，随工作时所处的 PV 值而上下，如当 PV 值在 2.5MPa·m/s 左右时，其使用寿命约为 200 小时，而当 PV 值在 0.1MPa·m/s 时，其使用寿命可在 10000 小时以上(详见表)


SF-2 衬套的加油保养周期 R 约为寿命的一半左右。例如当 PV=2.5MPa·m/s 时，要求每隔 100 小时必须加油保养一次。

◎When SF-2 bush is installed with application of grease such as lithium-based or silicone grease, its service life varies from the PV value under working condition, for instance, when PV value is about 2.5MPa·m/s, its service life will be about 200hr; when PV value is 0.1MPa·m/s, its service life can be above 10,000hr (see the table for details)

The cycle R of lubrication maintenance of SF-2 bush is about the half of its service life. For instance, when PV=25MPa·m/s, it is required to be oil-lubricated every 100hr.

SF-2 边界润滑轴承标准公制尺寸

SF-2 Marginal-Lubrication Bearings Standard Metric Size



单位 Unit: mm

d	D	相配轴径 Shaft Dia. f ₇	座孔 Housing H7	壁厚 Wall Thickness		油孔 Oil bore H	f ₁	f ₂	L ⁰ _{-0.40}									
				最小 Min.	最大 Max.				10	15	20	25	30	35	40	45	50	60
10	12	10 _{-0.022}	12 ^{+0.018}			4			1010	1015	1020							
12	14	12 _{-0.027}	14 ^{+0.018}			4			1210	1215	1220							
14	16	14 _{-0.027}	16 ^{+0.018}	0.955	0.980	4	0.6	0.3		1415	1420							
15	17	15 _{-0.027}	17 ^{+0.018}			4				1515	1520	1525						
16	18	16 _{-0.027}	18 ^{+0.018}			4				1615	1620	1625						
18	20	18 _{-0.027}	20 ^{+0.021}			4				1815	1820	1825						
20	23	20 _{-0.033}	23 ^{+0.021}			4				2015	2020	2025	2030					
22	25	22 _{-0.033}	25 ^{+0.021}	1.445	1.475	6	0.6	0.4		2215		2225						
25	28	25 _{-0.033}	28 ^{+0.021}			6				2515	2520	2525	2530					
28	32	28 _{-0.033}	32 ^{+0.025}			6					2820		2830					
30	34	30 _{-0.033}	34 ^{+0.025}	1.935	1.970	6	1.2	0.4			3020	3025	3030		3040			
35	39	35 _{-0.039}	39 ^{+0.025}			6					3520		3530	3535	3540			
40	44	40 _{-0.039}	44 ^{+0.025}			8					4020		4030		4040		4050	
45	50	45 _{-0.039}	50 ^{+0.025}			8					4520		4530		4540	4545	4550	
50	55	50 _{-0.039}	55 ^{+0.030}	2.415	2.460	8	1.8	0.6					5030		5040		5050	5060
55	60	55 _{-0.046}	60 ^{+0.030}			8						5530		5540		5550	5560	
60	65	60 _{-0.046}	65 ^{+0.030}			8							6030		6040		6050	6060



SF-2 边界润滑轴承标准公制尺寸

SF-2 Marginal-Lubrication Bearing Standard Metric Size

单位Unit: mm

d	D	相配轴径 Shaft Dia. f ₇	座孔 Housing H7	壁厚 Wall Thickness		油孔 Oil bore H	f ₁	f ₂	L ⁰ _{-0.40}								
				最小 Min.	最大 Max.				40	50	60	80	90	95	100	110	120
65	70	65 ^{-0.046}	70 ^{+0.030}			8			6540		6560						
70	75	70 ^{-0.046}	75 ^{+0.030}	2.415	2.460	8	1.8	0.6	7040	7050		7080					
75	80	75 ^{-0.046}	80 ^{+0.030}			8			7540		7560	7580					
80	85	80 ^{-0.046}	85 ^{+0.035}			9.5			8040		8060	8080					
85	90	85 ^{-0.054}	90 ^{+0.035}			9.5			8540		8560	8580					
90	95	90 ^{-0.054}	95 ^{+0.035}			9.5			9040		9060	9080	9090				
100	105	100 ^{-0.054}	105 ^{+0.035}			9.5	1.8	0.6		10050		10080		10095			
105	110	105 ^{-0.054}	110 ^{+0.035}			9.5					10560	10580		10595		105110	
110	115	110 ^{-0.054}	115 ^{+0.035}			9.5					11060	11080		11095		110110	
120	125	120 ^{-0.054}	125 ^{+0.040}			9.5					12060	12080				120110	
125	130	125 ^{-0.063}	130 ^{+0.040}			9.5					12560					125110	
130	135	130 ^{-0.063}	135 ^{+0.040}			9.5				13050	13060	13080			130100		
140	145	140 ^{-0.063}	145 ^{+0.040}			9.5				14050	14060	14080			140100		
150	155	150 ^{-0.063}	155 ^{+0.040}	2.385	2.450	9.5				15050	15060	15080			150100		
160	165	160 ^{-0.063}	165 ^{+0.040}			9.5				16050	16060	16080			160100		
170	175	170 ^{-0.063}	175 ^{+0.040}			9.5				17050		17080			170100		
180	185	180 ^{-0.063}	185 ^{+0.046}			9.5				18050	18060	18080			180100		
190	195	190 ^{-0.072}	195 ^{+0.046}			9.5	1.8	0.6		19050	19060	19080			190100		190120
200	205	200 ^{-0.072}	205 ^{+0.046}			9.5				20050	20060	20080			200100		200120
220	225	220 ^{-0.072}	225 ^{+0.046}			9.5				22050	22060	22080			220100		220120
240	245	240 ^{-0.072}	245 ^{+0.046}			9.5				24050	24060	24080			240100		240120
250	255	250 ^{-0.072}	255 ^{+0.052}			9.5				25050	25060	25080			250100		250120
260	265	260 ^{-0.081}	265 ^{+0.052}			9.5				26050	26060	26080			260100		260120
280	285	280 ^{-0.081}	285 ^{+0.052}			9.5				28050	28060	28080			280100		280120
300	305	300 ^{-0.081}	305 ^{+0.052}			9.5				30050	30060	30080			300100		300120

JINTAI SLIDE BEARING INTRODUCTION

Tel: 86-731-84770165
Fax: 86-731- 84770163

Http://www.slide-bearing.com/
E-mail:sales@slide-bearing.com



JINTAI SF-2 similar as GLYCODUR A dry sliding bushing . We produce washer as GLYCODUR A, GLYCO PXG A, in inch size bushing as GLYCODUR A, GLYCO PGZ A.

JINTAI SF-2 Bearing and GLYCODUR Bearing Standard Metric Size

单位 Unit: mm

JINTAI CODE	d*D*L(mm)	GLYCO CODE	JINTAI CODE	d*D*L(mm)	GLYCO CODE
SF-2 0203	2x3.5x3	PG 020303 A/3.5	SF-2 9090	90x95x90	PG 909590 A
SF-2 0205	2x3.5x5	PG 020305 A/3.5	SF-2 90100	90x95x100	PG 9095100 A
SF-2 0303	3x4.5x3	PG 030403 A/4.5	SF-2 9530	95x100x30	PG 9510030 A
SF-2 0304	3x4.5x4	PG 030404 A/4.5	SF-2 9540	95x100x40	PG 9510040 A
SF-2 0305	3x4.5x5	PG 030405 A/4.5	SF-2 9550	95x100x50	PG 9510050 A
SF-2 0306	3x4.5x6	PG 030406 A/4.5	SF-2 9560	95x100x60	PG 9510060 A
SF-2 0403	4x5.5x3	PG 040503 A/5.5	SF-2 9570	95x100x70	PG 9510070 A
SF-2 0404	4x5.5x4	PG 040504 A/5.5	SF-2 9580	95x100x80	PG 9510080 A
SF-2 0405	4x5.5x5	PG 040505 A/5.5	SF-2 9590	95x100x90	PG 9510090 A
SF-2 0406	4x5.5x6	PG 040506 A/5.5	SF-2 95100	95x100x100	PG 95100100 A
SF-2 0410	4x5.5x10	PG 040510 A/5.5	SF-2 10020	100x105x20	PG 10010520 A
SF-2 0505	5x7x5	PG 050705 A	SF-2 10030	100x105x30	PG 10010530 A
SF-2 0506	5x7x6	PG 050706 A	SF-2 10040	100x105x40	PG 10010540 A
SF-2 0507	5x7x7	PG 050707 A	SF-2 10050	100x105x50	PG 10010550 A
SF-2 0508	5x7x8	PG 050708 A	SF-2 10060	100x105x60	PG 10010560 A
SF-2 0510	5x7x10	PG 050710 A	SF-2 10070	100x105x70	PG 10010570 A
SF-2 0604	6x8x4	PG 060804 A	SF-2 10080	100x105x80	PG 10010580 A
SF-2 0605	6x8x5	PG 060805 A	SF-2 10090	100x105x90	PG 10010590 A
SF-2 0606	6x8x6	PG 060806 A	SF-2 100100	100x105x100	PG 100105100 A
SF-2 0608	6x8x8	PG 060808 A	SF-2 100115	100x105x115	PG 100105115 A
SF-2 0610	6x8x10	PG 060810 A	SF-2 10550	105x110x50	PG 10511050 A
SF-2 0705	7x9x5	PG 070905 A	SF-2 10560	105x110x60	PG 10511060 A
SF-2 0706	7x9x6	PG 070906 A	SF-2 10570	105x110x70	PG 10511070 A
SF-2 0708	7x9x8	PG 070908 A	SF-2 10580	105x110x80	PG 10511080 A
SF-2 0710	7x9x10	PG 070910 A	SF-2 10590	105x110x90	PG 10511090 A
SF-2 0715	7x9x15	PG 070915 A	SF-2 105100	105x110x100	PG 105110100 A
SF-2 0805	8x10x5	PG 081005 A	SF-2 105115	105x110x115	PG 105110115 A
SF-2 0806	8x10x6	PG 081006 A	SF-2 11050	110x115x50	PG 11011550 A
SF-2 0808	8x10x8	PG 081008 A	SF-2 11060	110x115x60	PG 11011560 A
SF-2 0810	8x10x10	PG 081010 A	SF-2 11070	110x115x70	PG 11011570 A
SF-2 0812	8x10x12	PG 081012 A	SF-2 11080	110x115x80	PG 11011580 A
SF-2 0815	8x10x15	PG 081015 A	SF-2 11090	110x115x90	PG 11011590 A
SF-2 0820	8x10x20	PG 081020 A	SF-2 11095	110x115x95	PG 11011595 A
SF-2 0908	9x11x8	PG 091108 A	SF-2 110100	110x115x100	PG 110115100 A
SF-2 0909	9x11x9	PG 091109 A	SF-2 110115	110x115x115	PG 110115115 A
SF-2 0910	9x11x10	PG 091110 A	SF-2 11550	115x120x50	PG 11512050 A
SF-2 1005	10x12x5	PG 101205 A	SF-2 11560	115x120x60	PG 11512060 A
SF-2 1006	10x12x6	PG 101206 A	SF-2 11570	115x120x70	PG 11512070 A
SF-2 1008	10x12x8	PG 101208 A	SF-2 11580	115x120x80	PG 11512080 A
SF-2 1009	10x12x9	PG 101209 A	SF-2 11590	115x120x90	PG 11512090 A
SF-2 1010	10x12x10	PG 101210 A	SF-2 115100	115x120x100	PG 115120100 A
SF-2 1012	10x12x12	PG 101212 A	SF-2 115115	115x120x115	PG 115120115 A
SF-2 1015	10x12x15	PG 101215 A	SF-2 12050	120x125x50	PG 12012550 A
SF-2 1020	10x12x20	PG 101220 A	SF-2 12060	120x125x60	PG 12012560 A
SF-2 1108	11x13x8	PG 111308 A	SF-2 12070	120x125x70	PG 12012570 A
SF-2 1109	11x13x9	PG 111309 A	SF-2 12080	120x125x80	PG 12012580 A
SF-2 1110	11x13x10	PG 111310 A	SF-2 12090	120x125x90	PG 12012590 A
SF-2 1112	11x13x12	PG 111312 A	SF-2 120100	120x125x100	PG 120125100 A
SF-2 1206	12x14x6	PG 121406 A	SF-2 120120	120x125x120	PG 120125120 A
SF-2 1208	12x14x8	PG 121408 A	SF-2 12550	125x130x50	PG 12513050 A
SF-2 1210	12x14x10	PG 121410 A	SF-2 12560	125x130x60	PG 12513060 A
SF-2 1212	12x14x12	PG 121412 A	SF-2 12570	125x130x70	PG 12513070 A
SF-2 1214	12x14x14	PG 121414 A	SF-2 12580	125x130x80	PG 12513080 A
SF-2 1215	12x14x15	PG 121415 A	SF-2 12590	125x130x90	PG 12513090 A
SF-2 1216	12x14x16	PG 121416 A	SF-2 125100	125x130x100	PG 125130100 A
SF-2 1220	12x14x20	PG 121420 A	SF-2 125115	125x130x115	PG 125130115 A
SF-2 1225	12x14x25	PG 121425 A	SF-2 13060	130x135x60	PG 13013560 A
SF-2 1308	13x15x8	PG 131508 A	SF-2 13070	130x135x70	PG 13013570 A
SF-2 1309	13x15x9	PG 131509 A	SF-2 13080	130x135x80	PG 13013580 A
SF-2 1310	13x15x10	PG 131510 A	SF-2 13090	130x135x90	PG 13013590 A


SF-2 1312	13x15x12	PG 131512 A	SF-2 130100	130x135x100	PG 130135100 A
SF-2 1315	13x15x15	PG 131515 A	SF-2 130120	130x135x120	PG 130135120 A
SF-2 1320	13x15x20	PG 131520 A	SF-2 13560	135x140x60	PG 13514060 A
SF-2 1325	13x15x25	PG 131525 A	SF-2 13570	135x140x70	PG 13514070 A
SF-2 1408	14x16x08	PG 141608 A	SF-2 13580	135x140x80	PG 13514080 A
SF-2 1410	14x16x10	PG 141610 A	SF-2 13590	135x140x90	PG 13514090 A
SF-2 1412	14x16x12	PG 141612 A	SF-2 135100	135x140x100	PG 135140100 A
SF-2 1415	14x16x15	PG 141615 A	SF-2 135120	135x140x120	PG 135140120 A
SF-2 1420	14x16x20	PG 141620 A	SF-2 14060	140x145x60	PG 14014560 A
SF-2 1422	14x16x22	PG 141622 A	SF-2 14070	140x145x70	PG 14014570 A
SF-2 1425	14x16x25	PG 141625 A	SF-2 14080	140x145x80	PG 14014580 A
SF-2 1508	15x17x8	PG 151708 A	SF-2 14090	140x145x90	PG 14014590 A
SF-2 1510	15x17x10	PG 151710 A	SF-2 140100	140x145x100	PG 140145100 A
SF-2 1512	15x17x12	PG 151712 A	SF-2 14560	145x150x60	PG 14515060 A
SF-2 1515	15x17x15	PG 151715 A	SF-2 14570	145x150x70	PG 14515070 A
SF-2 1518	15x17x18	PG 151718 A	SF-2 14580	145x150x80	PG 14515080 A
SF-2 1520	15x17x20	PG 151720 A	SF-2 14590	145x150x90	PG 14515090 A
SF-2 1525	15x17x25	PG 151725 A	SF-2 145100	145x150x100	PG 145150100 A
SF-2 1608	16x18x8	PG 161808 A	SF-2 145120	145x150x120	PG 145150120 A
SF-2 1610	16x18x10	PG 161810 A	SF-2 15050	150x155x50	PG 15015550 A
SF-2 1612	16x18x12	PG 161812 A	SF-2 15060	150x155x60	PG 15015560 A
SF-2 1615	16x18x15	PG 161815 A	SF-2 15070	150x155x70	PG 15015570 A
SF-2 1618	16x18x18	PG 161818 A	SF-2 15080	150x155x80	PG 15015580 A
SF-2 1620	16x18x20	PG 161820 A	SF-2 15090	150x155x90	PG 15015590 A
SF-2 1625	16x18x25	PG 161825 A	SF-2 150100	150x155x100	PG 150155100 A
SF-2 1630	16x18x30	PG 161830 A	SF-2 15550	155x160x50	PG 15516050 A
SF-2 1708	17x19x8	PG 171908 A	SF-2 15560	155x160x60	PG 15516060 A
SF-2 1710	17x19x10	PG 171910 A	SF-2 15570	155x160x70	PG 15516070 A
SF-2 1712	17x19x12	PG 171912 A	SF-2 15580	155x160x80	PG 15516080 A
SF-2 1715	17x19x15	PG 171915 A	SF-2 15590	155x160x90	PG 15516090 A
SF-2 1718	17x19x18	PG 171918 A	SF-2 155100	155x160x100	PG 155160100 A
SF-2 1720	17x19x20	PG 171920 A	SF-2 16050	160x165x50	PG 16016550 A
SF-2 1725	17x19x25	PG 171925 A	SF-2 16060	160x165x60	PG 16016560 A
SF-2 1808	18x20x8	PG 182008 A	SF-2 16070	160x165x70	PG 16016570 A
SF-2 1810	18x20x10	PG 182010 A	SF-2 16080	160x165x80	PG 16016580 A
SF-2 1812	18x20x12	PG 182012 A	SF-2 16090	160x165x90	PG 16016590 A
SF-2 1815	18x20x15	PG 182015 A	SF-2 160100	160x165x100	PG 160165100 A
SF-2 1820	18x20x20	PG 182020 A	SF-2 160110	160x165x110	PG 160165110 A
SF-2 1825	18x20x25	PG 182025 A	SF-2 160120	160x165x120	PG 160165120 A
SF-2 1830	18x20x30	PG 182030 A	SF-2 160130	160x165x130	PG 160165130 A
SF-2 1815a	18x21x15	PG 182115 A	SF-2 160140	160x165x140	PG 160165140 A
SF-2 1820a	18x21x20	PG 182120 A	SF-2 160150	160x165x150	PG 160165150 A
SF-2 1825a	18x21x25	PG 182125 A	SF-2 16560	165x170x60	PG 16517060 A
SF-2 2010a	20x22x10	PG 202210 A	SF-2 16570	165x170x70	PG 16517070 A
SF-2 2012a	20x22x12	PG 202212 A	SF-2 16580	165x170x80	PG 16517080 A
SF-2 2015a	20x22x15	PG 202215 A	SF-2 16590	165x170x90	PG 16517090 A
SF-2 2020a	20x22x20	PG 202220 A	SF-2 165100	165x170x100	PG 165170100 A
SF-2 2025a	20x22x25	PG 202225 A	SF-2 165110	165x170x110	PG 165170110 A
SF-2 2030a	20x22x30	PG 202230 A	SF-2 165120	165x170x120	PG 165170120 A
SF-2 2035a	20x22x35	PG 202235 A	SF-2 165130	165x170x130	PG 165170130 A
SF-2 2040a	20x22x40	PG 202240 A	SF-2 165140	165x170x140	PG 165170140 A
SF-2 2008	20x23x8	PG 202308 A	SF-2 165150	165x170x150	PG 165170150 A
SF-2 2010	20x23x10	PG 202310 A	SF-2 17060	170x175x60	PG 17017560 A
SF-2 2012	20x23x12	PG 202312 A	SF-2 17070	170x175x70	PG 17017570 A
SF-2 2015	20x23x15	PG 202315 A	SF-2 17080	170x175x80	PG 17017580 A
SF-2 2020	20x23x20	PG 202320 A	SF-2 17090	170x175x90	PG 17017590 A
SF-2 2025	20x23x25	PG 202325 A	SF-2 170100	170x175x100	PG 170175100 A
SF-2 2030	20x23x30	PG 202330 A	SF-2 170110	170x175x110	PG 170175110 A
SF-2 2035	20x23x35	PG 202335 A	SF-2 170120	170x175x120	PG 170175120 A
SF-2 2040	20x23x40	PG 202340 A	SF-2 170130	170x175x130	PG 170175130 A
SF-2 2210	22x25x10	PG 222510 A	SF-2 170140	170x175x140	PG 170175140 A
SF-2 2212	22x25x12	PG 222512 A	SF-2 170150	170x175x150	PG 170175150 A
SF-2 2215	22x25x15	PG 222515 A	SF-2 17560	175x180x60	PG 17518060 A
SF-2 2220	22x25x20	PG 222520 A	SF-2 17570	175x180x70	PG 17518070 A
SF-2 2225	22x25x25	PG 222525 A	SF-2 17580	175x180x80	PG 17518080 A
SF-2 2230	22x25x30	PG 222530 A	SF-2 17590	175x180x90	PG 17518090 A
SF-2 2235	22x25x35	PG 222535 A	SF-2 175100	175x180x100	PG 175180100 A
SF-2 2238	22x25x38	PG 222538 A	SF-2 175110	175x180x110	PG 175180110 A
SF-2 2240	22x25x40	PG 222540 A	SF-2 175120	175x180x120	PG 175180120 A
SF-2 2245	22x25x45	PG 222545 A	SF-2 175130	175x180x130	PG 175180130 A
SF-2 2250	22x25x50	PG 222550 A	SF-2 175140	175x180x140	PG 175180140 A
SF-2 2410	24x27x10	PG 242710 A	SF-2 175150	175x180x150	PG 175180150 A
SF-2 2412	24x27x12	PG 242712 A	SF-2 18060	180x185x60	PG 18018560 A
SF-2 2415	24x27x15	PG 242715 A	SF-2 18070	180x185x70	PG 18018570 A
SF-2 2420	24x27x20	PG 242720 A	SF-2 18080	180x185x80	PG 18018580 A
SF-2 2425	24x27x25	PG 242725 A	SF-2 18090	180x185x90	PG 18018590 A
SF-2 2428	24x27x28	PG 242728 A	SF-2 180100	180x185x100	PG 180185100 A
SF-2 2430	24x27x30	PG 242730 A	SF-2 180110	180x185x110	PG 180185110 A
SF-2 2432	24x27x32	PG 242732 A	SF-2 180120	180x185x120	PG 180185120 A
SF-2 2435	24x27x35	PG 242735 A	SF-2 180130	180x185x130	PG 180185130 A
SF-2 2438	24x27x38	PG 242738 A	SF-2 180140	180x185x140	PG 180185140 A
SF-2 2440	24x27x40	PG 242740 A	SF-2 180150	180x185x150	PG 180185150 A
SF-2 2450	24x27x50	PG 242750 A	SF-2 18560	185x190x60	PG 18519060 A
SF-2 2410b	24x28x10	PG 242810 A	SF-2 18570	185x190x70	PG 18519070 A
SF-2 2412b	24x28x12	PG 242812 A	SF-2 18580	185x190x80	PG 18519080 A
SF-2 2415b	24x28x15	PG 242815 A	SF-2 18590	185x190x90	PG 18519090 A

SF-2 2420b	24x28x20	PG 242820 A	SF-2 185100	185x190x100	PG 185190100 A
SF-2 2425b	24x28x25	PG 242825 A	SF-2 185110	185x190x110	PG 185190110 A
SF-2 2428b	24x28x28	PG 242828 A	SF-2 185120	185x190x120	PG 185190120 A
SF-2 2430b	24x28x30	PG 242830 A	SF-2 185130	185x190x130	PG 185190130 A
SF-2 2432b	24x28x32	PG 242832 A	SF-2 185140	185x190x140	PG 185190140 A
SF-2 2435b	24x28x35	PG 242835 A	SF-2 185150	185x190x150	PG 185190150 A
SF-2 2438b	24x28x38	PG 242838 A	SF-2 19060	190x195x60	PG 19019560 A
SF-2 2440b	24x28x40	PG 242840 A	SF-2 19070	190x195x70	PG 19019570 A
SF-2 2450b	24x28x50	PG 242850 A	SF-2 19080	190x195x80	PG 19019580 A
SF-2 2510	25x28x10	PG 252810 A	SF-2 19090	190x195x90	PG 19019590 A
SF-2 2512	25x28x12	PG 252812 A	SF-2 190100	190x195x100	PG 190195100 A
SF-2 2515	25x28x15	PG 252815 A	SF-2 190110	190x195x110	PG 190195110 A
SF-2 2520	25x28x20	PG 252820 A	SF-2 190120	190x195x120	PG 190195120 A
SF-2 2525	25x28x25	PG 252825 A	SF-2 190130	190x195x130	PG 190195130 A
SF-2 2528	25x28x28	PG 252828 A	SF-2 190140	190x195x140	PG 190195140 A
SF-2 2530	25x28x30	PG 252830 A	SF-2 190150	190x195x150	PG 190195150 A
SF-2 2532	25x28x32	PG 252832 A	SF-2 19560	195x200x60	PG 19520060 A
SF-2 2535	25x28x35	PG 252835 A	SF-2 19570	195x200x70	PG 19520070 A
SF-2 2540	25x28x40	PG 252840 A	SF-2 19580	195x200x80	PG 19520080 A
SF-2 2550	25x28x50	PG 252850 A	SF-2 19590	195x200x90	PG 19520090 A
SF-2 2560	25x28x60	PG 252860 A	SF-2 195100	195x200x100	PG 195200100 A
SF-2 2610	26x30x10	PG 263010 A	SF-2 195110	195x200x110	PG 195200110 A
SF-2 2612	26x30x12	PG 263012 A	SF-2 195120	195x200x120	PG 195200120 A
SF-2 2615	26x30x15	PG 263015 A	SF-2 195130	195x200x130	PG 195200130 A
SF-2 2620	26x30x20	PG 263020 A	SF-2 195140	195x200x140	PG 195200140 A
SF-2 2625	26x30x25	PG 263025 A	SF-2 195150	195x200x150	PG 195200150 A
SF-2 2630	26x30x30	PG 263030 A	SF-2 20060	200x205x60	PG 20020560 A
SF-2 2635	26x30x35	PG 263035 A	SF-2 20070	200x205x70	PG 20020570 A
SF-2 2640	26x30x40	PG 263040 A	SF-2 20080	200x205x80	PG 20020580 A
SF-2 2650	26x30x50	PG 263050 A	SF-2 20090	200x205x90	PG 20020590 A
SF-2 2810	28x32x10	PG 283210 A	SF-2 200100	200x205x100	PG 200205100 A
SF-2 2812	28x32x12	PG 283212 A	SF-2 200110	200x205x110	PG 200205110 A
SF-2 2815	28x32x15	PG 283215 A	SF-2 200120	200x205x120	PG 200205120 A
SF-2 2820	28x32x20	PG 283220 A	SF-2 200130	200x205x130	PG 200205130 A
SF-2 2825	28x32x25	PG 283225 A	SF-2 200140	200x205x140	PG 200205140 A
SF-2 2830	28x32x30	PG 283230 A	SF-2 200150	200x205x150	PG 200205150 A
SF-2 2832	28x32x32	PG 283232 A	SF-2 20560	205x210x60	PG 20521060 A
SF-2 2835	28x32x35	PG 283235 A	SF-2 20570	205x210x70	PG 20521070 A
SF-2 2840	28x32x40	PG 283240 A	SF-2 20580	205x210x80	PG 20521080 A
SF-2 3010	30x34x10	PG 303410 A	SF-2 20590	205x210x90	PG 20521090 A
SF-2 3012	30x34x12	PG 303412 A	SF-2 205100	205x210x100	PG 205210100 A
SF-2 3015	30x34x15	PG 303415 A	SF-2 205110	205x210x110	PG 205210110 A
SF-2 3020	30x34x20	PG 303420 A	SF-2 205120	205x210x120	PG 205210120 A
SF-2 3025	30x34x25	PG 303425 A	SF-2 205130	205x210x130	PG 205210130 A
SF-2 3028	30x34x28	PG 303428 A	SF-2 205140	205x210x140	PG 205210140 A
SF-2 3030	30x34x30	PG 303430 A	SF-2 205150	205x210x150	PG 205210150 A
SF-2 3032	30x34x32	PG 303432 A	SF-2 21060	210x215x60	PG 21021560 A
SF-2 3035	30x34x35	PG 303435 A	SF-2 21070	210x215x70	PG 21021570 A
SF-2 3038	30x34x38	PG 303438 A	SF-2 21080	210x215x80	PG 21021580 A
SF-2 3040	30x34x40	PG 303440 A	SF-2 21090	210x215x90	PG 21021590 A
SF-2 3045	30x34x45	PG 303445 A	SF-2 210100	210x215x100	PG 210215100 A
SF-2 3050	30x34x50	PG 303450 A	SF-2 210110	210x215x110	PG 210215110 A
SF-2 3210	32x36x10	PG 323610 A	SF-2 210120	210x215x120	PG 210215120 A
SF-2 3212	32x36x12	PG 323612 A	SF-2 210130	210x215x130	PG 210215130 A
SF-2 3215	32x36x15	PG 323615 A	SF-2 210140	210x215x140	PG 210215140 A
SF-2 3218	32x36x18	PG 323618 A	SF-2 210150	210x215x150	PG 210215150 A
SF-2 3220	32x36x20	PG 323620 A	SF-2 21560	215x220x60	PG 21522060 A
SF-2 3225	32x36x25	PG 323625 A	SF-2 21570	215x220x70	PG 21522070 A
SF-2 3230	32x36x30	PG 323630 A	SF-2 21580	215x220x80	PG 21522080 A
SF-2 3235	32x36x35	PG 323635 A	SF-2 21590	215x220x90	PG 21522090 A
SF-2 3240	32x36x40	PG 323640 A	SF-2 215100	215x220x100	PG 215220100 A
SF-2 3245	32x36x45	PG 323645 A	SF-2 215110	215x220x110	PG 215220110 A
SF-2 3250	32x36x50	PG 323650 A	SF-2 215120	215x220x120	PG 215220120 A
SF-2 3410	34x38x10	PG 343810 A	SF-2 215130	215x220x130	PG 215220130 A
SF-2 3412	34x38x12	PG 343812 A	SF-2 215140	215x220x140	PG 215220140 A
SF-2 3415	34x38x15	PG 343815 A	SF-2 215150	215x220x150	PG 215220150 A
SF-2 3420	34x38x20	PG 343820 A	SF-2 22060	220x225x60	PG 22022560 A
SF-2 3425	34x38x25	PG 343825 A	SF-2 22070	220x225x70	PG 22022570 A
SF-2 3430	34x38x30	PG 343830 A	SF-2 22080	220x225x80	PG 22022580 A
SF-2 3435	34x38x35	PG 343835 A	SF-2 22090	220x225x90	PG 22022590 A
SF-2 3440	34x38x40	PG 343840 A	SF-2 220100	220x225x100	PG 220225100 A
SF-2 3445	34x38x45	PG 343845 A	SF-2 220110	220x225x110	PG 220225110 A
SF-2 3510	35x39x10	PG 353910 A	SF-2 220120	220x225x120	PG 220225120 A
SF-2 3512	35x39x12	PG 353912 A	SF-2 220130	220x225x130	PG 220225130 A
SF-2 3515	35x39x15	PG 353915 A	SF-2 220140	220x225x140	PG 220225140 A
SF-2 3520	35x39x20	PG 353920 A	SF-2 220150	220x225x150	PG 220225150 A
SF-2 3525	35x39x25	PG 353925 A	SF-2 22560	225x230x60	PG 22523060 A
SF-2 3530	35x39x30	PG 353930 A	SF-2 22570	225x230x70	PG 22523070 A
SF-2 3535	35x39x35	PG 353935 A	SF-2 22580	225x230x80	PG 22523080 A
SF-2 3540	35x39x40	PG 353940 A	SF-2 22590	225x230x90	PG 22523090 A
SF-2 3545	35x39x45	PG 353945 A	SF-2 225100	225x230x100	PG 225230100 A
SF-2 3550	35x39x50	PG 353950 A	SF-2 225110	225x230x110	PG 225230110 A
SF-2 3610	36x40x10	PG 364010 A	SF-2 225120	225x230x120	PG 225230120 A
SF-2 3612	36x40x12	PG 364012 A	SF-2 225130	225x230x130	PG 225230130 A
SF-2 3615	36x40x15	PG 364015 A	SF-2 225140	225x230x140	PG 225230140 A
SF-2 3620	36x40x20	PG 364020 A	SF-2 23060	230x235x60	PG 23023560 A
SF-2 3625	36x40x25	PG 364025 A	SF-2 23070	230x235x70	PG 23023570 A
SF-2 3630	36x40x30	PG 364030 A	SF-2 23080	230x235x80	PG 23023580 A

SF-2 3635	36x40x35	PG 364035 A	SF-2 23090	230x235x90	PG 23023590 A
SF-2 3640	36x40x40	PG 364040 A	SF-2 230100	230x235x100	PG 230235100 A
SF-2 3645	36x40x45	PG 364045 A	SF-2 230110	230x235x110	PG 230235110 A
SF-2 3650	36x40x50	PG 364050 A	SF-2 230120	230x235x120	PG 230235120 A
SF-2 3812	38x42x12	PG 384212 A	SF-2 230130	230x235x130	PG 230235130 A
SF-2 3815	38x42x15	PG 384215 A	SF-2 230140	230x235x140	PG 230235140 A
SF-2 3820	38x42x20	PG 384220 A	SF-2 230150	230x235x150	PG 230235150 A
SF-2 3825	38x42x25	PG 384225 A	SF-2 23560	235x240x60	PG 23524060 A
SF-2 3830	38x42x30	PG 384230 A	SF-2 23570	235x240x70	PG 23524070 A
SF-2 3835	38x42x35	PG 384235 A	SF-2 23580	235x240x80	PG 23524080 A
SF-2 3840	38x42x40	PG 384240 A	SF-2 23590	235x240x90	PG 23524090 A
SF-2 3845	38x42x45	PG 384245 A	SF-2 235100	235x240x100	PG 235240100 A
SF-2 3850	38x42x50	PG 384250 A	SF-2 235110	235x240x110	PG 235240110 A
SF-2 3855	38x42x55	PG 384255 A	SF-2 235120	235x240x120	PG 235240120 A
SF-2 3860	38x42x60	PG 384260 A	SF-2 235130	235x240x130	PG 235240130 A
SF-2 4012	40x44x12	PG 404412 A	SF-2 235140	235x240x140	PG 235240140 A
SF-2 4015	40x44x15	PG 404415 A	SF-2 235150	235x240x150	PG 235240150 A
SF-2 4020	40x44x20	PG 404420 A	SF-2 24060	240x245x60	PG 24024560 A
SF-2 4025	40x44x25	PG 404425 A	SF-2 24070	240x245x70	PG 24024570 A
SF-2 4030	40x44x30	PG 404430 A	SF-2 24080	240x245x80	PG 24024580 A
SF-2 4035	40x44x35	PG 404435 A	SF-2 24090	240x245x90	PG 24024590 A
SF-2 4040	40x44x40	PG 404440 A	SF-2 240100	240x245x100	PG 240245100 A
SF-2 4045	40x44x45	PG 404445 A	SF-2 240110	240x245x110	PG 240245110 A
SF-2 4050	40x44x50	PG 404450 A	SF-2 240120	240x245x120	PG 240245120 A
SF-2 4055	40x44x55	PG 404455 A	SF-2 240130	240x245x130	PG 240245130 A
SF-2 4060	40x44x60	PG 404460 A	SF-2 240140	240x245x140	PG 240245140 A
SF-2 4212	42x46x12	PG 424612 A	SF-2 240150	240x245x150	PG 240245150 A
SF-2 4215	42x46x15	PG 424615 A	SF-2 24560	245x250x60	PG 24525060 A
SF-2 4220	42x46x20	PG 424620 A	SF-2 24570	245x250x70	PG 24525070 A
SF-2 4225	42x46x25	PG 424625 A	SF-2 24580	245x250x80	PG 24525080 A
SF-2 4230	42x46x30	PG 424630 A	SF-2 24590	245x250x90	PG 24525090 A
SF-2 4235	42x46x35	PG 424635 A	SF-2 245100	245x250x100	PG 245250100 A
SF-2 4240	42x46x40	PG 424640 A	SF-2 245110	245x250x110	PG 245250110 A
SF-2 4245	42x46x45	PG 424645 A	SF-2 245120	245x250x120	PG 245250120 A
SF-2 4250	42x46x50	PG 424650 A	SF-2 245130	245x250x130	PG 245250130 A
SF-2 4255	42x46x55	PG 424655 A	SF-2 245140	245x250x140	PG 245250140 A
SF-2 4260	42x46x60	PG 424660 A	SF-2 245150	245x250x150	PG 245250150 A
SF-2 4412	44x48x12	PG 444812 A	SF-2 25060	250x255x60	PG 25025560 A
SF-2 4415	44x48x15	PG 444815 A	SF-2 25070	250x255x70	PG 25025570 A
SF-2 4420	44x48x20	PG 444820 A	SF-2 25080	250x255x80	PG 25025580 A
SF-2 4425	44x48x25	PG 444825 A	SF-2 25090	250x255x90	PG 25025590 A
SF-2 4430	44x48x30	PG 444830 A	SF-2 250100	250x255x100	PG 250255100 A
SF-2 4435	44x48x35	PG 444835 A	SF-2 250110	250x255x110	PG 250255110 A
SF-2 4440	44x48x40	PG 444840 A	SF-2 250120	250x255x120	PG 250255120 A
SF-2 4445	44x48x45	PG 444845 A	SF-2 250130	250x255x130	PG 250255130 A
SF-2 4450	44x48x50	PG 444850 A	SF-2 250140	250x255x140	PG 250255140 A
SF-2 4455	44x48x55	PG 444855 A	SF-2 250150	250x255x150	PG 250255150 A
SF-2 4460	44x48x60	PG 444860 A	SF-2 25560	255x260x60	PG 25526060 A
SF-2 4515	45x50x15	PG 455015 A	SF-2 25570	255x260x70	PG 25526070 A
SF-2 4520	45x50x20	PG 455020 A	SF-2 25580	255x260x80	PG 25526080 A
SF-2 4525	45x50x25	PG 455025 A	SF-2 25590	255x260x90	PG 25526090 A
SF-2 4530	45x50x30	PG 455030 A	SF-2 255100	255x260x100	PG 255260100 A
SF-2 4535	45x50x35	PG 455035 A	SF-2 255110	255x260x110	PG 255260110 A
SF-2 4540	45x50x40	PG 455040 A	SF-2 255120	255x260x120	PG 255260120 A
SF-2 4545	45x50x45	PG 455045 A	SF-2 255130	255x260x130	PG 255260130 A
SF-2 4550	45x50x50	PG 455050 A	SF-2 255140	255x260x140	PG 255260140 A
SF-2 4555	45x50x55	PG 455055 A	SF-2 255150	255x260x150	PG 255260150 A
SF-2 4560	45x50x60	PG 455060 A	SF-2 26060	260x265x60	PG 26026560 A
SF-2 5015	50x55x15	PG 505515 A	SF-2 26070	260x265x70	PG 26026570 A
SF-2 5020	50x55x20	PG 505520 A	SF-2 26080	260x265x80	PG 26026580 A
SF-2 5025	50x55x25	PG 505525 A	SF-2 26090	260x265x90	PG 26026590 A
SF-2 5030	50x55x30	PG 505530 A	SF-2 260100	260x265x100	PG 260265100 A
SF-2 5035	50x55x35	PG 505535 A	SF-2 260110	260x265x110	PG 260265110 A
SF-2 5040	50x55x40	PG 505540 A	SF-2 260120	260x265x120	PG 260265120 A
SF-2 5045	50x55x45	PG 505545 A	SF-2 260130	260x265x130	PG 260265130 A
SF-2 5050	50x55x50	PG 505550 A	SF-2 260140	260x265x140	PG 260265140 A
SF-2 5055	50x55x55	PG 505555 A	SF-2 260150	260x265x150	PG 260265150 A
SF-2 5060	50x55x60	PG 505560 A	SF-2 26560	265x270x60	PG 26527060 A
SF-2 5065	50x55x65	PG 505565 A	SF-2 26570	265x270x70	PG 26527070 A
SF-2 5070	50x55x70	PG 505570 A	SF-2 26580	265x270x80	PG 26527080 A
SF-2 5515	55x60x15	PG 556015 A	SF-2 26590	265x270x90	PG 26527090 A
SF-2 5520	55x60x20	PG 556020 A	SF-2 265100	265x270x100	PG 265270100 A
SF-2 5525	55x60x25	PG 556025 A	SF-2 265110	265x270x110	PG 265270110 A
SF-2 5530	55x60x30	PG 556030 A	SF-2 265120	265x270x120	PG 265270120 A
SF-2 5535	55x60x35	PG 556035 A	SF-2 265130	265x270x130	PG 265270130 A
SF-2 5540	55x60x40	PG 556040 A	SF-2 265140	265x270x140	PG 265270140 A
SF-2 5545	55x60x45	PG 556045 A	SF-2 265150	265x270x150	PG 265270150 A
SF-2 5550	55x60x50	PG 556050 A	SF-2 27060	270x275x60	PG 27027560 A
SF-2 5555	55x60x55	PG 556055 A	SF-2 27070	270x275x70	PG 27027570 A
SF-2 5560	55x60x60	PG 556060 A	SF-2 27080	270x275x80	PG 27027580 A
SF-2 5565	55x60x65	PG 556065 A	SF-2 27090	270x275x90	PG 27027590 A
SF-2 5570	55x60x70	PG 556070 A	SF-2 270100	270x275x100	PG 270275100 A
SF-2 6015	60x65x15	PG 606515 A	SF-2 270110	270x275x110	PG 270275110 A
SF-2 6020	60x65x20	PG 606520 A	SF-2 270120	270x275x120	PG 270275120 A
SF-2 6025	60x65x25	PG 606525 A	SF-2 270130	270x275x130	PG 270275130 A
SF-2 6030	60x65x30	PG 606530 A	SF-2 270140	270x275x140	PG 270275140 A

SF-2 6035	60x65x35	PG 606535 A	SF-2 270150	270x275x150	PG 270275150 A
SF-2 6040	60x65x40	PG 606540 A	SF-2 27540	275x280x40	PG 27528040 A
SF-2 6045	60x65x45	PG 606545 A	SF-2 27560	275x280x60	PG 27528060 A
SF-2 6050	60x65x50	PG 606550 A	SF-2 27570	275x280x70	PG 27528070 A
SF-2 6055	60x65x55	PG 606555 A	SF-2 27580	275x280x80	PG 27528080 A
SF-2 6060	60x65x60	PG 606560 A	SF-2 27590	275x280x90	PG 27528090 A
SF-2 6065	60x65x65	PG 606565 A	SF-2 275100	275x280x100	PG 275280100 A
SF-2 6070	60x65x70	PG 606570 A	SF-2 275110	275x280x110	PG 275280110 A
SF-2 6075	60x65x75	PG 606575 A	SF-2 275120	275x280x120	PG 275280120 A
SF-2 6080	60x65x80	PG 606580 A	SF-2 275130	275x280x130	PG 275280130 A
SF-2 6085	60x65x85	PG 606585 A	SF-2 275140	275x280x140	PG 275280140 A
SF-2 6325	63x68x25	PG 636825 A	SF-2 275150	275x280x150	PG 275280150 A
SF-2 6090	60x65x90	PG 606590 A	SF-2 28060	280x285x60	PG 28028560 A
SF-2 6515	65x70x15	PG 657015 A	SF-2 28070	280x285x70	PG 28028570 A
SF-2 6520	65x70x20	PG 657020 A	SF-2 28080	280x285x80	PG 28028580 A
SF-2 6530	65x70x30	PG 657030 A	SF-2 28090	280x285x90	PG 28028590 A
SF-2 6535	65x70x35	PG 657035 A	SF-2 280100	280x285x100	PG 280285100 A
SF-2 6540	65x70x40	PG 657040 A	SF-2 280110	280x285x110	PG 280285110 A
SF-2 6550	65x70x50	PG 657050 A	SF-2 280120	280x285x120	PG 280285120 A
SF-2 6560	65x70x60	PG 657060 A	SF-2 280130	280x285x130	PG 280285130 A
SF-2 6570	65x70x70	PG 657070 A	SF-2 280140	280x285x140	PG 280285140 A
SF-2 6580	65x70x80	PG 657080 A	SF-2 280150	280x285x150	PG 280285150 A
SF-2 6590	65x70x90	PG 657090 A	SF-2 28560	285x290x60	PG 28529060 A
SF-2 7015	70x75x15	PG 707515 A	SF-2 28570	285x290x70	PG 28529070 A
SF-2 7020	70x75x20	PG 707520 A	SF-2 28580	285x290x80	PG 28529080 A
SF-2 7025	70x75x25	PG 707525 A	SF-2 28590	285x290x90	PG 28529090 A
SF-2 7030	70x75x30	PG 707530 A	SF-2 285100	285x290x100	PG 285290100 A
SF-2 7040	70x75x40	PG 707540 A	SF-2 285110	285x290x110	PG 285290110 A
SF-2 7045	70x75x45	PG 707545 A	SF-2 285120	285x290x120	PG 285290120 A
SF-2 7050	70x75x50	PG 707550 A	SF-2 285130	285x290x130	PG 285290130 A
SF-2 7060	70x75x60	PG 707560 A	SF-2 285140	285x290x140	PG 285290140 A
SF-2 7070	70x75x70	PG 707570 A	SF-2 285150	285x290x150	PG 285290150 A
SF-2 7080	70x75x80	PG 707580 A	SF-2 29060	290x295x60	PG 29029560 A
SF-2 7090	70x75x90	PG 707590 A	SF-2 29070	290x295x70	PG 29029570 A
SF-2 7530	75x80x30	PG 758030 A	SF-2 29080	290x295x80	PG 29029580 A
SF-2 7540	75x80x40	PG 758040 A	SF-2 29090	290x295x90	PG 29029590 A
SF-2 7550	75x80x50	PG 758050 A	SF-2 290100	290x295x100	PG 290295100 A
SF-2 7560	75x80x60	PG 758060 A	SF-2 290110	290x295x110	PG 290295110 A
SF-2 7570	75x80x70	PG 758070 A	SF-2 290120	290x295x120	PG 290295120 A
SF-2 7580	75x80x80	PG 758080 A	SF-2 290130	290x295x130	PG 290295130 A
SF-2 7590	75x80x90	PG 758090 A	SF-2 290140	290x295x140	PG 290295140 A
SF-2 8025	80x85x25	PG 808525 A	SF-2 290150	290x295x150	PG 290295150 A
SF-2 8030	80x85x30	PG 808530 A	SF-2 29540	295x300x40	PG 29530040 A
SF-2 8040	80x85x40	PG 808540 A	SF-2 29560	295x300x60	PG 29530060 A
SF-2 8050	80x85x50	PG 808550 A	SF-2 29570	295x300x70	PG 29530070 A
SF-2 8060	80x85x60	PG 808560 A	SF-2 29580	295x300x80	PG 29530080 A
SF-2 8070	80x85x70	PG 808570 A	SF-2 29590	295x300x90	PG 29530090 A
SF-2 8080	80x85x80	PG 808580 A	SF-2 295100	295x300x100	PG 295300100 A
SF-2 8090	80x85x90	PG 808590 A	SF-2 295110	295x300x110	PG 295300110 A
SF-2 80100	80x85x100	PG 8085100 A	SF-2 295120	295x300x120	PG 295300120 A
SF-2 8530	85x90x30	PG 859030 A	SF-2 295130	295x300x130	PG 295300130 A
SF-2 8540	85x90x40	PG 859040 A	SF-2 295140	295x300x140	PG 295300140 A
SF-2 8550	85x90x50	PG 859050 A	SF-2 295150	295x300x150	PG 295300150 A
SF-2 8560	85x90x60	PG 859060 A	SF-2 30060	300x305x60	PG 30030560 A
SF-2 8570	85x90x70	PG 859070 A	SF-2 30070	300x305x70	PG 30030570 A
SF-2 8580	85x90x80	PG 859080 A	SF-2 30080	300x305x80	PG 30030580 A
SF-2 8590	85x90x90	PG 859090 A	SF-2 30090	300x305x90	PG 30030590 A
SF-2 85100	85x90x100	PG 8590100 A	SF-2 300100	300x305x100	PG 300305100 A
SF-2 9020	90x95x20	PG 909520 A	SF-2 300110	300x305x110	PG 300305110 A
SF-2 9025	90x95x25	PG 909525 A	SF-2 300120	300x305x120	PG 300305120 A
SF-2 9030	90x95x30	PG 909530 A	SF-2 300130	300x305x130	PG 300305130 A
SF-2 9040	90x95x40	PG 909540 A	SF-2 300140	300x305x140	PG 300305140 A
SF-2 9050	90x95x50	PG 909550 A	SF-2 300150	300x305x150	PG 300305150 A
SF-2 9060	90x95x60	PG 909560 A			
SF-2 9070	90x95x70	PG 909570 A			
SF-2 9080	90x95x80	PG 909580 A			



SF-1WD/SF-2WD 止推垫片标准公制尺寸 SF-1WD/SF-2WD Thrust Washer Standard Metric Size



单位 Unit: mm

轴径 Axle	型号规格 Designation	垫片尺寸 Washer Dimension				安装尺寸 Installation Size			
		d +0.25	D -0.25	T -0.05	M ± 0.125	h ^{+0.40} _{+0.10}	t ± 0.20	D ₁ +0.12	
8	WD 10	10	20	1.5	15	1.5	1.0	20	
10	WD 12	12	24		18			24	
12	WD 14	14	26		20			26	
14	WD 16	16	30		23	30			
16	WD 18	18	32		25	2.0			32
18	WD 20	20	36		28				36
20	WD 22	22	38	2.0	30	3.0			38
22	WD 24	24	42		33				42
24	WD 26	26	44		35				44
26	WD 28	28	48		38				48
30	WD 32	32	54		43		54		
36	WD 38	38	62		50		62		
40	WD 42	42	66		54	4.0		66	
46	WD 48	48	74		61			74	
50	WD 52	52	78		65	1.5		78	
60	WD 62	62	90		76			90	

SF-1/SF-2 板材标准公制尺寸 SF-1/SF-2 Strip Standard Metric Size



单位 Unit: mm

代号 Code number	长度(L) ± 1	宽度(W) ± 1	壁厚(T)-0.05
SF-1/SF-2	500	150	1.0
SF-1/SF-2	500	150	1.5
SF-1/SF-2	500	150	2.0
SF-1/SF-2	500	150	2.5

JF-800 系列双金属轴承 JF-800 Bimetal Bearings



◎JF-800 以碳钢为基体，表面烧结铜粉，适用于高载低速下的旋 转、摇摆运动，铜粉面可根据要求加工出各种油孔、油槽。目前已 广泛使用于矿山机械、汽车、摩托车、建筑机械、农用机械、轧钢 机械等。

◎Steel backed Lead bronze lined bearing material for lubricated applications, high load capacity and good fatigue properties, have been widely used in automotive, common industrial like steering gear, power steering, pedal bushes, king-pin bushes, tailgate pivots, mechanical handling, lifting equipment, hydraulic motors, agricultural machines etc.

成分、特性、用途

Chemical Compositions, Characteristics and Application

材料型号 Types of Material	铜合金牌号 Specifications of Bronze alloy	化学成分% Chemical Compositions	合金层硬度 Alloy Hrdness	特性与用途 Characteristics and Application
JF-930	CuSn6.5P0.1	铜锡磷 Cu Sn P 93 6.0~7.0 0.1~0.25	HB(60-90)	无铅 Lead Free
JF-850	CuSn6Zn6Pb3	铜锡锌铅 Cu Sn Zn Pb 85 6 6 3	HB(40-80)	启动电机 Starting Motor
JF-800	CuPb10Sn10	铜铅锡 Cu Pb Sn Zn 80 10 10	HB(60-90)	在铜合金中最强的一种，应用范围广 The strongest material type, wide application scope.
JF-750	CuPb24Sn1	铜铅锡 Cu Pb Sn 75 24 1	HB(45-70)	连杆摇臂 Link Arm
JF-720	CuPb24Sn4	铜铅锡 Cu Pb Sn 72 24 4	HB(45-70)	连杆摇臂 Link Arm

技术参数 Tech.Data

最大荷载 Max.Load	静承载 Static	250N/mm ²	屈服强度 Yield strength	240N/mm ²
	动承载 Dynamic	140N/mm ²	使用温度 Temp.limit	-40℃~+250℃
最高线速度 Max. linear speed		2m/s	摩擦系数 Friction Coeff.	0.08~0.20
最大PV值 PV limit		2.8N/mm ² ·m/s	导热系数 Thermal conductivity	60W(m·k)-1
抗剪切强度 Shear resistance strength		350N/mm ²	导热系数 Thermal conductivity	14·10 ⁻⁶ K ⁻¹


JF-800 双金属内孔加工与不可加工厚度公差

Wall Thickness of The Machinable and Non-machinable Bore of JF-800 Bearings and Their Tolerances

公称厚度 Nominal Thickness	内孔不可加工厚度公差 Tolerances of Series B (non-machinable)	内孔可加工厚度公差 Tolerances of Series C (non-machinable)
1	-0.025	+0.25 +0.15 +0.25
1.5	-0.030	+0.15 +0.25 +0.15
2	-0.035	+0.25 +0.15 +0.30
2.5	-0.040	+0.15 +0.30 +0.15
3	-0.045	+0.30 +0.15 +0.30
3.5	-0.050	+0.30 +0.15

JF-800 双金属轴承标准公制尺寸

JF-800 Bimetal Bearings Standard Metric Size



单位 unit:mm

d	D	壁厚 Wall Thickness	外径 O.D Tolerance	内径公差 I.D.(H8) Tolerance	配合座孔 H7 Housing Bore	轴径 f ₇ Journal Diameter	f ₁	f ₂	L -0.40											
									10	15	20	25	30	40	50	60	80	90	100	
10	12	1 -0.025	12 ^{+0.065} _{+0.030}	10 ^{+0.022} _{+0.000}	10 ^{-0.013} _{-0.028}	12 ^{+0.018}	0.5	0.3	1010	1015	1020									
12	14		14 ^{+0.065} _{+0.030}	12 ^{+0.027} _{+0.000}	12 ^{-0.016} _{-0.034}	14 ^{+0.018}	0.5	0.3	1210	1215	1220									
14	16		16 ^{+0.065} _{+0.030}	14 ^{+0.027} _{+0.000}	14 ^{-0.016} _{-0.034}	16 ^{+0.018}	0.5	0.3	1410	1415	1420									
15	17		17 ^{+0.065} _{+0.030}	15 ^{+0.027} _{+0.000}	15 ^{-0.016} _{-0.034}	17 ^{+0.018}	0.5	0.3	1510	1515	1520									
16	18			18 ^{+0.075} _{+0.035}	16 ^{+0.027} _{+0.000}	16 ^{-0.016} _{-0.034}	18 ^{+0.018}	0.8	0.4	1610	1615	1620								
18	20		20 ^{+0.075} _{+0.035}	18 ^{+0.033} _{+0.000}	18 ^{-0.016} _{-0.034}	20 ^{+0.021}	0.8	0.4	1810	1815	1820	1825								
20	23	1.5 -0.030	23 ^{+0.075} _{+0.035}	20 ^{+0.033} _{+0.000}	20 ^{-0.020} _{-0.041}	23 ^{+0.021}	0.8	0.4	2010	2015	2020	2025								
22	25		25 ^{+0.075} _{+0.035}	22 ^{+0.033} _{+0.000}	22 ^{-0.020} _{-0.041}	25 ^{+0.021}	0.8	0.4	2210	2215	2220	2225								
24	27		27 ^{+0.075} _{+0.035}	24 ^{+0.033} _{+0.000}	24 ^{-0.020} _{-0.041}	27 ^{+0.021}	1.0	0.5	2410	2415	2420		2430							
25	28		28 ^{+0.075} _{+0.035}	25 ^{+0.033} _{+0.000}	25 ^{-0.020} _{-0.041}	28 ^{+0.021}	1.0	0.5		2515	2520	2525	2530							
26	30			30 ^{+0.075} _{+0.035}	26 ^{+0.033} _{+0.000}	26 ^{-0.020} _{-0.041}	30 ^{+0.021}	1.0	0.5		2615	2620	2625	2630						
28	32		32 ^{+0.085} _{+0.045}	28 ^{+0.033} _{+0.000}	28 ^{-0.020} _{-0.041}	32 ^{+0.025}	1.0	0.5		2815	2820	2825	2830	2840						
30	34	2 -0.035	34 ^{+0.085} _{+0.045}	30 ^{+0.039} _{+0.000}	30 ^{-0.020} _{-0.041}	34 ^{+0.025}	1.2	0.6		3015	3020	3025	3030	3040						
32	36		36 ^{+0.085} _{+0.045}	32 ^{+0.039} _{+0.000}	32 ^{-0.025} _{-0.050}	36 ^{+0.025}	1.2	0.6		3215	3220	3225	3230	3240						
35	39		39 ^{+0.085} _{+0.045}	35 ^{+0.039} _{+0.000}	35 ^{-0.025} _{-0.050}	39 ^{+0.025}	1.2	0.6			3520	3525	3530	3540	3550					
38	42		42 ^{+0.085} _{+0.045}	38 ^{+0.039} _{+0.000}	38 ^{-0.025} _{-0.050}	42 ^{+0.025}	1.2	0.6			3825	3825	3830	3840	3850					
40	44		44 ^{+0.085} _{+0.045}	40 ^{+0.039} _{+0.000}	40 ^{-0.025} _{-0.050}	44 ^{+0.025}	1.2	0.6			4020	4025	4030	4040	4050					
45	50		50 ^{+0.085} _{+0.045}	45 ^{+0.039} _{+0.000}	45 ^{-0.025} _{-0.050}	50 ^{+0.025}	1.5	1.0			4520	4525	4530	4540	4550					
50	55		55 ^{+0.100} _{+0.050}	50 ^{+0.039} _{+0.000}	50 ^{-0.025} _{-0.050}	55 ^{+0.030}	1.5	1.0					5030	5040	5050	5060				
55	60	2.5 -0.040	60 ^{+0.100} _{+0.050}	55 ^{+0.046} _{+0.000}	55 ^{-0.030} _{-0.060}	60 ^{+0.030}	1.5	1.0					5530	5540	5550	5560				
60	65		65 ^{+0.100} _{+0.050}	60 ^{+0.046} _{+0.000}	60 ^{-0.030} _{-0.060}	65 ^{+0.030}	1.5	1.0					6030	6040	6050	6060				
65	70		70 ^{+0.100} _{+0.050}	65 ^{+0.046} _{+0.000}	65 ^{-0.030} _{-0.060}	70 ^{+0.030}	1.5	1.0					6530	6540	6550	6560				
70	75		75 ^{+0.100} _{+0.050}	70 ^{+0.046} _{+0.000}	70 ^{-0.030} _{-0.060}	75 ^{+0.030}	1.5	1.0					7030	7040	7050	7060	7080			
75	80			80 ^{+0.100} _{+0.050}	75 ^{+0.046} _{+0.000}	75 ^{-0.030} _{-0.060}	80 ^{+0.035}	1.5	1.0					7530	7540	7550	7560			
80	85		85 ^{+0.120} _{+0.070}	80 ^{+0.054} _{+0.000}	80 ^{-0.030} _{-0.060}	85 ^{+0.035}	1.5	1.0						8040	8050	8060	8080			

FB090 系列青铜卷制轴承 **FB090 Bronze-Wrapped Bearings**



产品概述

◎FB090 系列青铜卷制轴承套是我公司在钢-铜铅双金属轴套产品基础上开发设计的新一代轴套。该产品在国外应用十分普遍，随着我国引进机械的设备新机种的日益增多，设计师们寻找新型摩擦材料、轴套的要求也日益需要，因此该产品在我们机械制造中有着广泛应用领域和实用价值。

◎FB090 系列轴套最大特点是薄壁结构，不占据很大的装配空间。轴套材料采用特殊配方高密度铜合金带材。它与传统的铺型铜套相比，具有密度高、无气缩孔、承载能力大，又有耐磨耐疲劳等优点。轴套制造采用先进的工装模具，可在带材摩擦面上加工出适用各种工程条件的油穴、油坑、油槽，从而使轴套在使用可储存大量润滑油脂，延长加油间隔时间，有效的提高了使用寿命。

◎FB090 系列轴承广泛应用与农业机械、建筑机械、工程机械、汽车行业等。

Product Overview

◎FB090 series bronze rolled bushing is our new generation bushing based upon steel-bronze lead double metal bushings. This product is widely applied overseas. With the increase of our country's introduction of foreign machineries, designer's requirements on new abrasive materials and bushings are accordingly increasing. Therefore, our products see a wide application scope and practical value in machinery production.

◎The major feature of FB090 series bushing is their thin-wall structure, which doesn't take up too large assembly space. Specially formulated high-density bronze alloy bands are used for the building of the bushing, which, compared with traditional bushings, is featured in the high

density, no shrinkage blowholes, high load sustainability and anti-wearing and anti-fatigue. The production of the bushing is by means of advanced fixture and molds, able to make oil holes, hole dents and grooves on the friction surfaces of the bands to suit various engineering applications, making it possible for the bushing to store large amount of lubricating grease when working. Therefore, the lubrication interval is prolonged and the service hours are effectively lengthened.

◎FB090 series bearings are widely used in applications such as agricultural machineries, construction machineries, engineering machineries and automobile industry.

FB090 系列产品的优点

1. 节约大量铜材、节省车制铜套工时；
2. 与车制轴套、滚动轴承相比其重量轻、成本低；
3. 可在摩擦面加工出各种有穴、有坑、储存一定油脂，延长加油的时间是铜套的 5 倍
4. 极高的承载能力，特别是适用于粗糙的摩擦面： 可供产品：直套、止推垫片、翻边衬套、轴瓦、滑板、钢套组合件。

FB090 Product Benefits

1. Saving large amount of bronze material and save the working hours normally spent for lathing the bronze bushing.
2. Compared with lathed bushings and roller bearings, it is lights and more cost-effective.
3. Various holes and dents can be made on the friction surface for grease storage, prolonging the lubrication interval to 5 times as long as required by the bronze bushing.

4. Extremely high load sustainability, especially suitable for coarse abrasion surfaces.

Standard products available: straight bushings, thrust plates and pressure bearings.


Non-standard products available: straight bushings, thrust plates, planks, bearing bushings, slide plates and steel bushing assembly.

FB090 轴承简介 FB090 Bearing Introduction


材料结构 Material Structure

◎采用高密度青铜卷制成形或球形油袋、油穴特殊合成内部表面以减少磨损延长使用时间并且很好的做到防腐功能。


◎High-density bronze is rolled into shape or oil bags and oil holes are specially integrated into the inner surface to reduce the wearing and prolong the service hours. Besides, it has excellent anti-corrosion functions.



轴衬套内
Inside the bush of the shaft
菱形油穴 $r \leq \phi 22$
Rhomb oil holes $r \leq \phi 22$



轴衬套内
Inside the bush of the shaft
菱形油穴 $r > \phi 22$
Rhomb oil holes $r > \phi 22$



形成菱形
Forming a rhomb

化学成分 Chemical Composition

材料Material	铜 Cu	锡 Sn	磷 P	铅 Pb	锌 Zn
CuSn8	91.3%	8.5%	0.2%	-	-

物理特性 Physical Property

型号Type	密度Density	散热热胀Heat Emission and Expansion	热传导Heat Conducting	硬度Hardness	抗压强度Extensile	延伸率Extensile
FB090	8.8g/cm ³	$18.5 \times 10^{-2} \times K^{-1}$	58W(m·k)	90~120HB	470N/mm ²	40%

应用范围 Application scope

此系列轴承广泛应用与农用、建设机械以及工程机械等。

This series of bearing is widely applied to agricultural, construction and engineering machineries, etc.

油穴类别(依据 DIW1494/ISO3457)。

Categories of oil holes (As per to DIW1494/ISO3457)。

标准衬套公差 (依据 DIW W91/1503547) Standard tolerance for bushes (As per to DIW W91/1503547)

标准直径Standard Dia.	衬套外径尺寸O.D.Size	相配座孔Housing Bore	衬套内径尺寸I.D.Size	相配轴径Matching Shaft Diameter
10~18	+0.065 +0.030	+0.018 0	+0.046 0	- 0.016 - 0.043
18~30	+0.075 +0.035	+0.021 0	+0.052 0	- 0.020 - 0.020
30~50	+0.085 +0.045	+0.025 0	+0.062 0	- 0.025 - 0.064
50~80	+0.100 +0.055	+0.030 0	+0.074 0	- 0.030 - 0.076
80~120	+0.120 +0.070	+0.035 0	+0.087 0	- 0.036 - 0.090
120~180	+0.170 +0.100	+0.400 0	+0.100 0	- 0.043 - 0.106
180~250	+0.210 +0.130	+0.046 0	+0.115 0	- 0.050 - 0.122
250~315	+0.260 +0.170	+0.052 0	+0.130 0	- 0.056 - 0.137



FB092 系列青铜卷制轴承 FB092 Bronze-Wrapped Bearings

产品概述

◎FB092系列青铜卷制轴承是与FB090材料结构相同，我单位根据国外同类产品基础上开发出的新一代产品轴套，能改良产品设计、替代原有铜套，能降低采购成本，因此产品在我们机械制造中有着广泛实用价值和应用领域。

◎FB092系列轴套最大特点是薄壁结构，不占据很大的装配空间。轴套材料采用特殊配方高密度铜合金带材。它与传统的铺型铜套相

比，可在带材摩擦面上加工出适用各种工程条件的油穴、油坑、油槽，排列润滑通孔，从而使轴套在使用可储存大量润滑油脂，延长加油间隔时间，有效的提高了使用寿命。

◎FB092系列轴承广泛应用与农业机械、建筑机械、工程机械、高载低速场合等。

Product Overview

◎FB092 series bronze rolled bushing is our new generation bushing based upon steel-bronze lead double metal bushings. This product is widely applied overseas. With the increase of our country's introduction of foreign machineries, designer's requirements on new abrasive materials and bushings are accordingly increasing. Therefore, our products see a wide application scope and practical value in machinery production.

◎The major feature of FB092 series bushing is their thin-wall structure, which doesn't take up too large assembly space. Specially formulated high-density bronze alloy bands are used for the building of the bushing, which, compared with traditional bushings, is featured in the high

density, no shrinkage blowholes, high load sustainability and anti-wearing and anti-fatigue. The production of the bushing is by means of advanced fixture and molds, able to make oil holes, hole dents and grooves on the friction surfaces of the bands to suit various engineering applications, making it possible for the bushing to store large amount of lubricating grease when working. Therefore, the lubrication interval is prolonged and the service hours are effectively lengthened.

◎FB092 series bearings are widely used in applications such as agricultural machineries, construction machineries, engineering machineries and automobile industry.

FB092 系列产品的优点

1. 节约大量铜材、节省车制铜套工时；
 2. 与车制轴套、滚动轴承相比其重量轻、成本低；
 3. 可在摩擦面加工出各种有穴、有坑、储存一定油脂，延长加油的时间是铜套的5倍
 4. 极高的承载能力，特别是适用于粗糙的摩擦面；
- 可供标准产品：直套、翻边衬套、组合钢套。

FB092 Product Benefits


1. Saving large amount of bronze material and save the working hours normally spent for lathing the bronze bushing.
2. Compared with lathed bushings and roller bearings, it is lights and more cost-effective.
3. Various holes and dents can be made on the friction surface for grease storage, prolonging the lubrication interval to 5 times as long as required by the bronze bushing.

4. Extremely high load sustainability, especially suitable for coarse abrasion surfaces.


Standard products available: straight bushings, thrust plates and pressure bearings.

Non-standard products available: straight bushings, thrust plates, planks, bearing bushings, slide plates and steel bushing assembly.

FB092 轴承简介 FB092 Bearing Introduction



轴承内部 球形
内径 $r \leq 25$



轴承球形 内径
 $r > 25$

化学成分 Chemical Composition

材料Material	铜 Cu	锡 Sn	磷 P	铅 Pb	锌 Zn
CuSn8	91.3%	8.5%	0.2%	-	-

物理特性 Physical Property

型号 Type	密度 Density	散热热胀 Heat Emission and Expansion	热传导 Heat Conducting	硬度 Hardness	抗压强度 Extensile	延伸率 Extensile
FB092	8.8g/cm ³	$18.5 \times 10^{-2} \times K^1$	58W(m·k)	90~120HB	470N/mm ²	40%

应用范围 Application scope

此系列轴承广泛应用与农用、建设机械以及工程机械等。

This series of bearing is widely applied to agricultural, construction and engineering machineries, etc.

标准衬套公差 (依据 DIW W91/1503547) Standard tolerance for bushes (As per to DIW W91/1503547)

标准直径 Standard Dia.	衬套外径尺寸 O.D.Size	相配座孔 Housing Bore	衬套内径尺寸 I.D.Size	相配轴径 Matching Shaft Diameter
10~18	+0.065 +0.030	+0.018 0	+0.046 0	- 0.016 - 0.043
18~30	+0.075 +0.035	+0.021 0	+0.052 0	- 0.020 - 0.020
30~50	+0.085 +0.045	+0.025 0	+0.062 0	- 0.025 - 0.064
50~80	+0.100 +0.055	+0.030 0	+0.074 0	- 0.030 - 0.076
80~120	+0.120 +0.070	+0.035 0	+0.087 0	- 0.036 - 0.090
120~180	+0.170 +0.100	+0.400 0	+0.100 0	- 0.043 - 0.106
180~250	+0.210 +0.130	+0.046 0	+0.115 0	- 0.050 - 0.122
250~315	+0.260 +0.170	+0.052 0	+0.130 0	- 0.056 - 0.137

FB09G 系列青铜卷制轴承 **FB09G Bronze-Wrapped Bearings**



材料结构 Material Structure

◎与FB090具有相同的生产工艺及使用场合，其基体为青铜基板，在其菱形油穴内填充了以石墨为主的固体润滑剂，使产品在起始运用阶段及过程中能有更低的摩擦系数，在短时间断油的情况下仍能保持良好的工作状态。因此被广泛使用在工程机械、齿轮箱传动部件、汽机车离合器等高载中速部位、户外高空设备的转动部位。

◎The same produce process and application except overlay the solid lubricants into the diamond shaped lubrication indents on the bearing surface, which will offer good friction at the start and process works and keep good condition even no oil giving at short time. So can be used in construction machines, gears, automotive clutch pads etc.

技术参数 Tech.Data

最大承载压力	Load capacity	140N/mm ²
适应温度范围	Temperature limit	-100℃~+250℃
最高滑动速度	Speed limit	1.5M/s
摩擦系数	Friction clef	0.06~0.25
允许最高PV值(干)	PV limit (dry)	2.6N/mm ² ·m/s
允许最高PV值(油)	PV limit (oil)	15N/mm ² ·m/s

可供形式 Availability

直套、止推垫片、滑板及其它非标品部件等。


Cylindrical bushes, thrust washers, strip and non-standard parts as the clients supplied drawing etc.

公差 Tolerance

一般推荐座孔公差为H7，轴径公差为f7。

Recommend housing tolerance H7 and the shaft as f7.

FB090/FB092/FB09G 青铜卷制轴承标准公制尺寸 FB090/FB092/FB09G Bronze-Wrapped Bearings Standard Metric Size



单位 Unit: mm

d	D	相配轴径 Shaft Dia. f ₇	座孔 Housing H7	壁厚 Wall Thickness		f ₁	f ₂	L ⁰ _{-0.40}										
				最小 Min.	最大 Max.			6	8	10	12	15	20	25	30	40	50	
6	8	6 ^{-0.013} _{-0.028}	8 ^{+0.015}	0.980	1.005	0.6	0.3	0606	0608	0610								
8	10	8 ^{-0.013} _{-0.028}	10 ^{+0.015}					0806	0808	0810	0812	0815						
10	12	10 ^{-0.016} _{-0.034}	12 ^{+0.018}					1006	1008	1010	1012	1015	1020					
12	14	12 ^{-0.016} _{-0.034}	14 ^{+0.018}					1206	1208	1210	1212	1215	1220	1225				
13	15	13 ^{-0.016} _{-0.034}	15 ^{+0.018}							1310			1320					
14	16	14 ^{-0.016} _{-0.034}	16 ^{+0.018}								1410	1412	1415	1420	1425			
15	17	15 ^{-0.016} _{-0.034}	17 ^{+0.018}									1510	1512	1515	1520	1525		
16	18	16 ^{-0.016} _{-0.034}	18 ^{+0.018}										1610	1612	1615	1620	1625	
17	19	17 ^{-0.016} _{-0.034}	19 ^{+0.021}	1.475	1.505	0.6	0.4			1710	1712		1720					
18	20	18 ^{-0.016} _{-0.034}	20 ^{+0.021}							1810	1812	1815	1820	1825				
20	23	20 ^{-0.020} _{-0.041}	23 ^{+0.021}							2010	2012	2015	2020	2025	2030			
22	25	22 ^{-0.020} _{-0.041}	25 ^{+0.021}							2210	2212	2215	2220	2225	2230			
24	27	24 ^{-0.020} _{-0.041}	27 ^{+0.021}									2415	2420	2425	2430			
25	28	25 ^{-0.020} _{-0.041}	28 ^{+0.021}						2510	2512	2515	2520	2525	2530	2540	2550		
28	32	28 ^{-0.020} _{-0.041}	32 ^{+0.025}	1.970	2.005	1.2	0.4					2815	2820	2825	2830	2840		
30	34	30 ^{-0.020} _{-0.041}	34 ^{+0.025}							3012	3015	3020	3025	3030	3040			
32	36	32 ^{-0.025} _{-0.050}	36 ^{+0.025}									3220		3230	3240			
35	39	35 ^{-0.025} _{-0.050}	39 ^{+0.025}								3512	3515	3520	3525	3530	3540	3550	
38	42	38 ^{-0.025} _{-0.050}	42 ^{+0.025}									3815			3830	3840		
40	44	40 ^{-0.025} _{-0.050}	44 ^{+0.025}							4012		4020	4025	4030	4040	4050		



FB090/FB092/FB09G 青铜卷制轴承标准公制尺寸

FB090/FB092/FB09G Bronze-Wrapped Bearings Standard Metric Size

单位Unit: mm


d	D	相配轴径 Shaft Dia. f ₇	座孔 Housing H7	壁厚 Wall Thickness		f ₁	f ₂	L ⁰ _{-0.40}											
				最小 Min.	最大 Max.			20	25	30	40	50	60	70	80	100	115		
45	50	45 ^{-0.025} _{-0.050}	50 ^{+0.025}					4520	4525	4530	4540	4550							
50	55	50 ^{-0.025} _{-0.050}	55 ^{+0.030}					5020		5030	5040	5050	5060						
55	60	55 ^{-0.030} _{-0.060}	60 ^{+0.030}							5530	5540	5550	5560						
60	65	60 ^{-0.030} _{-0.060}	65 ^{+0.030}	2.460	2.505	1.8	0.6			6030	6040	6050	6060	6070					
65	70	65 ^{-0.030} _{-0.060}	70 ^{+0.030}							6530	6540	6550	6560	6570					
70	75	70 ^{-0.030} _{-0.060}	75 ^{+0.030}								7040	7050	7060	7070	7080				
75	80	75 ^{-0.030}	80 ^{+0.030}							7530	7540	7550	7560	7570	7580				
80	85	80 ^{-0.035}	85 ^{+0.035}								8040	8050	8060	8070	8080	80100			
85	90	85 ^{-0.035}	90 ^{+0.035}								8540		8560		8580	85100			
90	95	90 ^{-0.035}	95 ^{+0.035}								9040	9050	9060		9080	90100			
95	100	95 ^{-0.035}	100 ^{+0.035}	2.440	2.490	1.8	0.6					9550	9560		9580	95100			
100	105	100 ^{-0.035}	105 ^{+0.035}									10050	10060		10080		100115		
105	110	105 ^{-0.035}	110 ^{+0.035}										10560		10580		105115		
110	115	110 ^{-0.035}	115 ^{+0.035}										11060		11080		110115		
120	125	120 ^{-0.035}	125 ^{+0.040}										12060		12080	120100			
125	130	125 ^{-0.040}	130 ^{+0.040}										12560			125100	125115		
130	135	130 ^{-0.040}	135 ^{+0.040}	2.415	2.465	1.8	0.6						13060		13080	130100			
140	145	140 ^{-0.040}	145 ^{+0.040}											14060		14080	140100		
150	155	150 ^{-0.040}	155 ^{+0.040}										15060		15080	150100			
160	165	160 ^{-0.040}	165 ^{+0.040}										16060		16080	160100	160115		
180	185	180 ^{-0.040}	185 ^{+0.046}	2.415	2.465	1.8	0.6								18080	180100			
190	195	190 ^{-0.046}	195 ^{+0.046}														19080	190100	
200	205	200 ^{-0.046}	205 ^{+0.046}														20080	200100	
220	225	220 ^{-0.046}	225 ^{+0.046}													20060		22080	220100
250	255	250 ^{-0.046}	255 ^{+0.052}												25080	250100			
260	265	260 ^{-0.052}	265 ^{+0.052}	2.415	2.465	1.8	0.6								26080	260100			
280	285	280 ^{-0.052}	285 ^{+0.052}														28080	280100	
300	305	300 ^{-0.052}	305 ^{+0.052}																

注：要求相配轴孔H7，轴径f7，衬套压入座孔后内孔值为H8。

Note: Shaft hole is required to be H7. Shaft diameter is f7. After bearing is installed, the inner hole should be H8.

FB090/FB092 青铜卷制翻边轴承标准公制尺寸

FB090/FB092 Bronze-Wrapped Flange Bearing Standard Metric Size



单位Unit: mm

d ₁	d ₂	d ₃	f ₁	f ₂	L ⁰ / _{-0.40}										
					15	20	25	30	35	40	50	60	70	80	90
25	28	35	0.8	0.4	2515	2520	2525								
30	34	45				3020	3025	3030							
35	39	50	1.0	0.6		3520	3525	3530	3535						
40	44	55					4025	4030	4035	4040					
45	50	60						4530	4535	4540	4550				
50	55	65						5030	5035	5040	5050				
55	60	70						5530	5535	5540	5550				
60	65	75	1.2	0.8				6030	6035	6040	6050	6060			
65	70	80						6530	6535	6540	6550	6560			
70	75	85							7035	7040	7050	7060	7070		
75	80	90							7535	7540	7550	7560	7570		
80	85	100							8035	8040	8050	8060	8070	8080	
90	95	110									9050	9060	9070	9080	9090
100	105	120									10050	10060	10070	10080	10090
110	115	130									11050	11060	11070	11080	11090
120	125	140									12050	12060	12070	12080	12090
130	135	155										13060	13070	13080	13090
140	145	165										14060	14070	14080	14090
150	155	180										15060	15070	15080	15090
160	165	190										16060	16070	16080	16090
170	175	200	1.4	0.8								17060	17070	17080	17090
180	185	215										18060	18070	18080	18090
190	195	225										19060	19070	19080	19090
200	205	235										20060	20070	20080	20090
225	230	260										22560	22570	22580	22590
250	255	290										25060	25070	25080	25090
265	270	305										26560	26570	26580	26590
285	290	325										28560	28570	28580	28590
300	305	340										30060	30070	30080	30090

FB08G 固体润滑卷制轴承

FB08G Solid-Lubricant-Embedded Wrapped Bearings



材料结构 Material Structure

◎FB08G固体润滑轴承是以JF-800双金属材料为基体，再埋入特殊固体润滑剂制作成的新型滑动轴承。由于高强度承载的合金材料作基体，并经过严格选择的高分子填充材料为耐磨剂，合理的螺旋角度菱形块状均布的润滑面，润滑面积达25%，因此，能发挥超群的低摩擦，良好的润滑性和抗磨损性免除加油。该产品已广泛应用于起重起、微型电机、升降机、吊车及冶金机械等行业。

◎FB08G is a kind of steel-lead bronze alloys based bearing, which is embedded with particular formulation of solid lubricants. Owing to the high strength, high load capacity and the spirally distributed diamond type of the embedded solid lubricant, the high temperature


resistant action as extraordinary exploited. The lubrication area of the bearing surface is being about 25%. This type of bearing is particularly applied in starting motor for automobiles, generators cranes and those machines in metallurgical industry.

技术参数 Tech.Data

最大承载压力	Load capacity	150N/mm ²
适应温度范围	Temperature limit	-100℃~+200℃
最高滑动速度	Speed limit	1.5M/s
摩擦系数	Friction clef	0.06~0.25
允许最高PV值(干)	PV limit (dry)	2.5N/mm ² ·m/s
允许最高PV值(油)	PV limit (oil)	15N/mm ² ·m/s

FB08G 固体润滑卷制轴承标准公制尺寸

FB08G Solid-Lubricant-Embedded Wrapped Bearings Standard Metric Size



单位 Unit: mm

d	D	f ₁	f ₂	L ⁰ _{-0.40}													
				10	15	20	25	30	35	40	50	60	70	80	90	100	
10	12	0.3	0.5	1010	1015	1020											
12	14			1210	1215	1220											
14	16			1410	1415	1420	1425										
15	17			1510	1515	1520	1525										
16	18			1610	1615	1620	1625										
18	20			1810	1815	1820	1825										
20	23	0.8	0.4	2210	2015	2020	2025										
22	25			2010	2215	2220	2225	2230									
24	27				2415	2420	2425	2430									
25	28				2515	2520	2525	2530									
28	32				2815	2820	2825	2830									
30	34	1.0	0.6		3015	3020	3025	3030	3035	3040							
32	36				3215	3220	3225	3230	3235	3240							
35	39				3515	3520	3525	3530	3535	3540							
40	44					4020	4025	4030	4035	4040	4050						
45	50					4520	4525	4530	4535	4540	4550						
50	55					5020	5025	5030	5035	5040	5050	5060					
55	60	1.2				5520	5525	5530	5535	5540	5550	5560					
60	65						6025	6030	6035	6040	6050	6060	6070				
65	70							6530	6535	6540	6560	6560	6570				
70	75							7030	7035	7040	7050	7060	7070	7080			
75	80							7530	7535	7540	7550	7560	7570	7580			
80	85							8030	8035	8040	8050	8060	8070	8080			
85	90										7550	8560	8570	8580	9590		
90	95										9050	9060	9070	9080	9090		
95	100	0.8									9550	9560	9570	9580	9590	951000	
100	105											10050	10060	10070	10080	10090	100100
105	110											10550	10560	10570	10580	10590	105100
110	115										11050	11060	11070	11080	11090	110100	
115	120	1.4										11550	11560	11570	11580	11590	115100
120	125												12060	12070	12080	12090	120100
125	130												12560	12570	12580	12590	125100
130	135												13060	13070	13080	13090	130100
135	140											13560	13570	13580	13590	135100	
140	145											14060	14070	14080	14090	140100	
145	150											14560	14570	14580	14590	145100	
150	155											15060	15070	15080	15090	150100	
155	160											15560	15570	15580	15590	155100	
160	165											16060	16070	16080	16090	160100	

JDB 固体镶嵌轴承 JDB Solid-lubricant-Inlaid Bearings



材料结构 Material Structure

铜合金镶嵌式固体润滑剂自润滑轴承，结合了铜合金的耐磨性及固体润滑剂的自润滑性能，使其在使用过程中无需加油维护。产品被广泛应用于高载、间歇性或摇摆运动，如汽机车生产流水线、水轮机、水库工作/事故门、塑胶机械、冲床周边设备等。根据使用的工况，可以提供各种类型的铜合金。


This material provides a maintenance-free bearing solution, particularly for high load, intermittent of oscillating motion. Solid lubricants within a bronze combines the strength of the bronze with the wear resistance and low friction. The application including automotive products line, water engineering, dam gate, plastic industries etc. Different bronze alloy type can be available according to the work condition.

技术参数 Tech.Data

最大承载	静承载 Static Load	250N/mm ²
Max. Load	动承载 Dynamic Load	100N/mm ²
最高线速度	干摩擦 Dry Friction	0.3m/s
Max linear speed	油摩擦 Oil Friction	1.0m/s
最大PV值 PV limit		1.65N/mm ² ·m/s
抗拉强度 Tensile strength		750N/mm ²

使用温度 Working temperature	-100℃~+300℃
摩擦系数 Abrasion coefficient	0.03~0.20
导热系数 Heat conducting coefficient	60W/(m·K) ⁻¹
热膨胀系数 Heat expansion coefficient	19·10 ⁻⁶ K ⁻¹
延伸率 Extensile rate	12%
硬度 Hardness	HB < 210

JDB 直固体镶嵌轴承标准公制尺寸 JDB Solid-lubricant-Inlaid Bearings Standard Metric Size



单位Unit: mm

d	D	内径 I.D. F7		外径 O.D. m6		L ^{-0.10} / _{-0.30}													
						8	10	12	15	16	20	25	30	35	40	50	60	70	80
8	12	8	+0.028 +0.013	12	+0.018 +0.007	081208	081210	081212	081215										
10	14	10		14		101408	101410	101412	101415		101420								
12	18	12		18			121810	121812	121815	121816	121820	121825	121830						
13	19	13		19			131910		131915	131916									
14	20	14	+0.034 +0.016	20	+0.021 +0.008		142010	142012	142015		142020	142025	142030						
15	21	15		21			152110	152112	152115	152116	152120	152125	152130						
16	22	16		22			162210	162212	162215	162216	162220	162225	162230	162235	162240				
18	24	18		24				182412	182415	182416	182420	182425	182430	182435	182440				
20	28	20		28			202810	202812	202815	202816	202820	202825	202830	202835	202840	202850			
22	32	22		32				223212	223215		223220	223225							
25	33	25		33				253312	253315	253316	253320	253325	253330	253335	253340	253350	253360		
30	38	30	+0.041 +0.020	38	+0.025 +0.009			303812	303815		303820	303825	303830	303835	303840	303850	303860		
35	45	35		45							354520	354525	354530	354535	354540	354550	354560		
40	50	40		50							405020	405025	405030	405035	405040	405050	405060	405070	405080
45	55	45		55									455530	455535	455540	455550	455560		
50	60	50		60									506030	506035	506040	506050	506060	506070	506080



JDB 直固体镶嵌轴承标准公制尺寸


JDB Solid-lubricant-Inlaid Bearings Standard Metric Size

单位Unit: mm

d	D	内径 I.D. F7		外径 O.D. m6		L ^{-0.10 -0.30}											
						30	35	40	50	60	70	80	100	120	130	140	150
50	62	50	+0.050 +0.025	62		506230	506235	506240	506250	506260	506270						
50	65	50		65		506530		506540	506550	506560	506570	506580	5065100				
55	70	55		70				557040	557050	557060	557070						
60	75	60		75	+0.030 +0.011	607430	607435	607440	607540	607460	607470	607480					
60	75	60		75		607530	607535	607540	607550	607560	607570	607580	6075100				
63	75	63		75						637560	637570	637580					
65	80	65		80					658050	658060	658070	658080					
70	85	70	+0.060 +0.030	85			708535	708540	708550	708560	708570	708580	7085100				
70	90	70		90					709050	709060	709070	709080					
75	90	75		90						759060	759070	759080	7590100				
75	95	75		95	+0.035 +0.013					759560	759570	759580	7595100				
80	96	80		96				809640	809560	809660	809670	809680	8096100	8096120			
80	100	80		100				8010040	8010050	8010060	8010070	8010080	80100100	80100120		80100140	
90	110	90		110		9011030			9011050	9011060	9011070	9011080	90110100	90110120			
100	120	100	+0.071 +0.036	120						10012060	10012070	10012080	100120100	100120120		100120140	
110	130	110		130									11013080	110130100	110130120		
120	140	120		140									12014080	120140100	120140120		120140140
125	145	125		145									125145100	125145120			
130	150	130		150	+0.040 +0.015								130150100		130150130		
140	160	140	+0.083 +0.043	160									140160100			140160140	
150	170	150		170									150170100				150170150
160	180	160		180									160180100				160180150

JFB 翻边轴承标准公制尺寸


JFB Flange Bearings Standard Metric Size



单位Unit: mm

d	D	内径 I.D. F7		外径 O.D. m6		F	L ₁	L ^{-0.10} / _{-0.30}									
								15	20	25	30	35	40	50	60	80	100
10	14	10	^{+0.040} / _{+0.025}	14	^{+0.034} / _{+0.023}	22	2	1015	1020								
12	18	12		18		25		1215	1220								
13	19	13		19		26		1315	1320								
14	20	14	^{+0.050} / _{+0.032}	20		27	3	1415	1420								
15	21	15		21	^{+0.041} / _{+0.028}	28		1515	1520	1525	1530						
16	22	16		22		29		1615	1620	1625	1630						
20	30	20		30		40			2020	2025	2030	2035					
25	35	25	^{+0.061} / _{+0.040}	35		45			2520	2525	2530	2535					
30	40	30		40	^{+0.050} / _{+0.034}	50			3020	3025	3030	3035	3040	3050			
35	45	35		45		60	5			3525	3530	3535	3540	3550			
40	50	40		50		65					4030	4035	4040	4050			
45	55	45	^{+0.075} / _{+0.050}	55		70					4530	4535	4540	4550	4560		
50	60	50		60	^{+0.060} / _{+0.041}	75							5050	5050	5060		
55	65	55		65		80							5540	5550	5560		
60	75	60		75	^{+0.062} / _{+0.043}	90							6040	6050	6060	6080	
70	85	70	^{+0.090} / _{+0.060}	85		105	7.5							7050	7060	7080	
75	90	75		90	^{+0.073} / _{+0.051}	110								7550	7560		
80	100	80		100		120									8060	8080	80100
100	120	100		120	^{+0.076} / _{+0.054}	150	10								10060	10080	100100
120	140	120	^{+0.107} / _{+0.072}	140	^{+0.088} / _{+0.063}	170									12060	12080	120100


JSP 滑块标准公制尺寸 JSP Sliding Plate Standard Metric Size



单位Unit: mm

型号规格 Designation	W	L	a	b	Sketch 图示
JSP 28 × 75	28	75	-	45	A
JSP 28 × 100		100		50	
JSP 28 × 150		150		100	
JSP 38 × 75	38	75	-	45	A
JSP 38 × 100		100		50	
JSP 38 × 150		150		100	
JSP 48 × 75	48	75	-	45	A
JSP 48 × 100		100		50	
JSP 48 × 125		125		75	
JSP 48 × 150	58	150	-	100	A
JSP 48 × 200		200		150	
JSP 58 × 75		75		45	
JSP 58 × 100	58	100	-	50	A
JSP 58 × 150		150		100	
JSP 75 × 75		75	-	25	A
JSP 75 × 100	75	100		50	
JSP 75 × 125		125		75	
JSP 75 × 150	100	150	50	100	A
JSP 75 × 200		200		150	
JSP 100 × 100		100		50	
JSP 100 × 125	100	125	50	75	A
JSP 100 × 150		150		100	
JSP 100 × 200		200		150	
JSP 100 × 250	125	250	50	200	B
JSP 100 × 300		300		200	
JSP 125 × 125		125		75	
JSP 125 × 150	125	150	50	100	B
JSP 125 × 200		200		150	
JSP 125 × 250		250		200	
JSP 125 × 300	150	300	100	200	B
JSP 125 × 350		350		200	
JSP 150 × 150		150		100	
JSP 150 × 200	150	200	100	150	B
JSP 150 × 250		250		200	

JTW 止推垫片标准公制尺寸 JTW Thrust Washer Standard Metric Size



单位Unit: mm

型号规格 Designation	ϕd	ϕD	$T_{-0.10}^0$	螺孔 Bolt Hole			
				ϕD_1	平头螺钉 Crop Bolt	ϕd_1	孔数 Bore Number
JTW 10	10.2	30		20			
JTW 12	12.2						
JTW 13	13.2	40		28			
JTW 14	14.2		3		M3	3.5	
JTW 15	15.2						
JTW 16	16.2	50		35			
JTW 18	18.2						2
JTW 20	20.2						
JTW 25	25.2	55	5	40	M5	6	
JTW 30	30.2	60		45			
JTW 35	35.2	70		50			
JTW 40	40.2	80	7	60			
JTW 45	45.3	90		70	M6	7	
JTW 50	50.3	100		75			
JTW 55	55.3	110	8	85			
JTW 60	60.3	120		90			
JTW 70	70.3	130		100			
JTW 75	75.3	140		110	M8	9	4
JTW 80	80.3	150	10	120			
JTW 90	90.5	170		140			
JTW 100	100.5	190		160	M10	11	
JTW 120	120.5	200		175			

FZ 直线轴承 FZ Ball Retainer Bearings



产品简介 Intruduction

◎FZH (铜基)、FZL (铝基)、FZP (树脂基) 钢球保持固, 分别以铜合金、硬铝合 金、POM 树脂为基体, 并在其外圆表面上, 加工出排列有序、大小适当, 形状特殊的孔 穴, 在其孔穴中镶入滚动轴承钢球。口采用最新的沟槽圆周锁球工艺, 有效地解决了传统 式锁球和压痕式锁球不能完全防止钢球脱落的难题。孔底加工出 90° 止口使钢球在孔内自 由转动而不脱落。由于钢球的直径大于保持圈的壁厚, 所以在使用时钢球高出保持圈内、 外圆表面, 直接与相配的孔与轴接触, 使基体(保持圈)浮于中间, 并且相配的孔与轴半径 之差小于钢球直径, 即钢球与之配合为过盈配合, 配合精度高, 轴与孔相对运动灵活。是 保持圈的更新换代产品。

◎FZH. FZL. FZP. ball retainer are as copper, aluminium, POM base. they are machined some regular holes and embedded the steel-ball into. The new work-craft will prevent the ball getting out of as old. as the ball diameter is larger than the retainer s thickness, so it will face to face directly with 90° guide bushing, that will bring high precision match now the ball retainer series items are designed to rotate on the post, as well as maintainits vertical motion. we believe this will give you the benefit of increasing accijracy.

优点与用途 Advantage And Use

◎传统的具有相对运动的孔与轴是有一定间隙的, 并孔与轴之间运动磨擦系数较大, 使用钢球保持圈后, 使轴与孔不直接接触, 而是通过中间微量过盈的钢球, 因而运动精度高, 滚动摩擦代替动摩擦, 滚动灵活, 摩擦系数小, 使用寿命长, 在既有转动、又有移动的场合, 用无油或加油的轴套与轴相配合, 虽然能满足, 但运动精度较低, 用滚动轴承, 只能满足轴相对转动的场合, 而钢球保持圈, 则上述二个条件均得到满足, 目前已广泛应用于冷冲模滚动模架、高精度机床、机床附件以及要求高精度轴向或轴径向同时运动场合。

◎As the traditional work-craft has some grudge between bushing with posts, and the coefficient of friction is larger. now we have changed the work-ways to steel-ball directly face to face guide bushing, so the precision is improved. it composes of both active roll and lower friction coefficient, now they have been widely used in punching machine, die machine, high precision machine which need rotation and vertical motion.


相配零件的要求 Installed Spares Requested

1. 导套: 材料 GCr15、YB9, 热处理, 硬度 HRC62~66, 技术条件按 GB/T12446 与轴配合应具有 0.01-0.02 径向过盈量, 表面粗糙度为^{0.05} 2. 轴: 材料 GCr15、YB9, 热处理, 硬度 HRC62~66, 技术条件按 GB/T12446, 轴的公差采用 h5, 表面粗糙度为^{0.05} 3. 测量: 用通用的测量手段 (气动量仪、外径千分尺、内径千分表等) 测量轴套和钢球 的尺寸偏差值, 即可求出配合后的过盈量, 即 $Y_{max} = d_{max} + 2d' - D_{min}$, 要求过盈量为 0.01-0.02mm


1. GUIDE BUSHING: MATERIAL GCr15, YB9, HEAT TREATMENT HRC62-66, TECHNIQUE CONDITION ACCORDING TO GB/T1 2446. REQUEST 0.01-0.02mm THE SURFACE ROUGHNESS IS^{0.05}

2. GUIDIE POSTS: MATRIAL GCr15, YB9, HEAT TREATMENT HRC62-66, THE TOLERANCE OF SHAFT IS h5, THE SURFACE ROUGHNESS IS^{0.05}

3. SIZE TEST: IT IS TESTED BY OUTSIDE MICROMETER & DIAL GAUGE AS USUAL. THE Y_{max} ($Y_{max} + 2d' - D_{min}$) REQUEST 0.01-0.02mm



FZ 钢球保持圈标准公制尺寸 FZ Ball Retainers Standard Metric Size



单位unit:mm

型号规格 Designation	D	H	d	E _N	M _N	球 BALLS	t	L
FZ(*)1950	19	50		12	8	96		5.75
FZ(*)1960		60			10	120		5.25
FZ(*)2050	20	50			8	96		5.75
FZ(*)2060		60			10	120		5.25
FZ(*) 2250	22	50	3	14	8	112	5.5	5.75
FZ(*) 2260		60			10	140		5.25
FZ(*)2360	23	60			10	208		5.25
FZ(*)2475	24	75			13	128		4.50
FZ(*)2550	25	50		16	8	112		5.75
FZ(*)2560		60			10	160		5.25
FZ(*)2575		75			13	208		4.50
FZ(*)2775	27	75			13	208		4.50
FZ(*)2860	28	60		14	8	112		7.25
FZ(*)2875		75			11	154		5.00
FZ(*)3060	30	60	4		8	112	6.5	7.25
FZ(*)3075		75			11	154		5.00
FZ(*)3260	32	60			8	128		7.25
FZ(*)3275		75			11	192		5.00
FZ(*)3390	36	90		16	13	208		6.00
FZ(*)3685		85			12	192		6.75
FZ(*)3690		90			13	208		6.00
FZ(*)3870	38	70			8	128		7.00
FZ(*)3890		90			11	176		5.00
FZ(*)4090	40	90			11	176		5.00
FZ(*)4590	45	90	5	18	11	198	8.0	5.00
FZ(*)45110		110			13	234		7.00
FZ(*)5090	50	90		20	11	220		5.00
FZ(*)50110		110			13	260		7.00
FZ(*)6090	60	90		22	11	242		5.00
FZ(*)60110		110			13	286		7.00
FZ(*)80130	80	130		28	15	420		9.00

注：FZ(*)为：FZH(铜基)、FZL(铝基)、FZP(树脂基)

Notes: FZ(*)： FZH (Bronze based) FZL (Aluminum based) FZP (Resin based)

FD 四氟软带 FD PTFE Soft Strips



材料结构 Material Structure

◎FD以PTFE为主材，以铜粉及其它高分子添加剂为辅的耐磨性材料。产品广泛运用化工行业、油压、油缸、汽摩减振器、机床导轨、印刷机械、纺织机械等轻载但需要自润滑的场合。产品如经过特殊处理，可粘帖于钢质或者橡胶面上，产品在使用过程中无爬行现象。

◎FD consist of PTFE with bronze powder and additive material, This material structure enables the final goods have more light and easy for install. It is widely been used in chemica lindustries, medicalindustries, fluid hydraulic industries, textile machines, OA machines, Door/window hinges etc.

技术参数 Tech.Data

最大承载	静承载 Static Load	30N/mm ²
Max. Load	动承载 Dynamic Load	20N/mm ²
使用温度 Temp. Limit		-40℃~+250℃
最高滑动速度	干摩擦 Dry Friction	0.5m/s
Tiptop Sliding Velocity	油摩擦 Oil Friction	2m/s
摩擦系数 Friction Coeff.		0.10-0.20
允许最高PV值 PV limit	干摩擦 Dry Friction	1.65N/mm ² ·m/s


FD 产品活塞环尺寸 Size of The Products

20×18×2	25×23.2×8	30×38.2×8
20×18×3	25×23×8	30×28×8
5×22.2×2.5	27×25×8	30×38.2×11.4
25×22×2.5	30×28×9	32×30.2×8

FD 产品带材尺寸 Strip Measurement of The Products

100×1.5	100×1	200×0.5
8×2.5	12×2.5	25×2.5
6.1×2.5	7.9×2.5	14.8×2.5
19.5×2.5	24.5×2.5	29.5×2.5

SF-1X 无油润滑材料




材料组织结构:

- | | |
|-----------------------------------|-------------------------------------|
| 1、聚四氟乙烯与铅的混合物 0.01~0.03mm | ■ 摩擦系数: 0.04~0.20 |
| 2、球形青铜粉: 0.2~0.3mm | ■ 导热系数: 13W/MK |
| 3、钢背: 0.5~3.03mm | ■ 使用温度范围: -195℃~270℃ |
| 4、电镀层: 镀锡层厚 0.005mm 或镀铜层厚 0.008mm | ■ 线膨胀系数: $11 \times 10^{-6} K^{-1}$ |

应用特点:

- 1、无油润滑或少油润滑场合, 耐磨性能好, 摩擦系数小, 使用寿命长。
- 2、有适量的弹塑性, 能将应力分布在较宽的接触面上。
- 3、静动摩擦系数相近, 能消除低速下的爬行。
- 4、对于对磨轴的硬度要求低, 未经调质处理的轴都可使用, 在运转构成中能形成转移膜, 起到保护对磨轴的作用, 无咬轴现象。
- 5、钢背可电镀多种金属, 可在腐蚀介质中使用, 目前已广泛应用于各种机械的滑动部位, 例如: 印刷机、纺织机、烟草机械、微电机、汽车、摩托车与农林机械等等。

SF-1T 齿轮石泵专用材料




材料组织结构:

- | | |
|-----------------------------------|-------------------------------------|
| 1、聚四氟乙烯与铅及其他填充混合物 0.01~0.03mm | ■ 摩擦系数: 0.03~0.18 |
| 2、球形青铜粉: 0.2~0.3mm | ■ 导热系数: 13W/MK |
| 3、钢背: 0.5~3.3mm | ■ 使用温度范围: -195℃~260℃ |
| 4、电镀层: 镀锡层厚 0.005mm 或镀铜层厚 0.008mm | ■ 线膨胀系数: $11 \times 10^{-6} K^{-1}$ |

应用特点:

- 1、在有油润滑条件下摩擦系数小而稳定。
- 2、耐磨性能好, 抗冲击性能好。
- 3、由此材料制作的衬套, 在流体润滑条件下 PV 值可达到 120N/mm²*m/s
- 4、目前已广泛运用于各种齿轮油泵、柱塞泵、叶片泵等场合, 对流体润滑或境界润滑条件下的中高压齿轮泵尤其使用。

SF-1P 往复运动材料




材料组织结构:

- | | |
|-----------------------------------|-------------------------------------|
| 1、聚四氟乙烯与铜混合物 0.02~0.04mm | ■ 摩擦系数: 0.04~0.20 |
| 2、球形青铜粉: 0.2~0.3mm | ■ 导热系数: 13W/MK |
| 3、钢背: 0.5~3.3mm | ■ 使用温度范围: -195℃~270℃ |
| 4、电镀层: 镀锡层厚 0.005mm 或镀铜层厚 0.008mm | ■ 线膨胀系数: $11 \times 10^{-6} K^{-1}$ |

应用特点:

- 1、具有在沾油情况下润滑能力强、耐磨性能好、保护油膜清晰的特点。
- 2、能较好的保护对轴表面不受磨损, 对往复运动场合较能适用。
- 3、应其含铅量很少, 故迎合了环保要求。
- 4、适用于摩托车减震器、各种液压油缸、液压马达、气动元件等领域。

SF-1W 无铅材料




材料组织结构:

- | | |
|-----------------------------------|--|
| 1、聚四氟乙烯与纤维混合物 0.01~0.03mm | ■ 摩擦系数: 0.04~0.20 |
| 2、球形青铜粉: 0.2~0.3mm | ■ 导热系数: 13W/MK |
| 3、钢背: 0.5~3.3mm | ■ 使用温度范围: -195℃ ~270℃ |
| 4、电镀层: 镀锡层厚 0.005mm 或镀铜层厚 0.008mm | ■ 线膨胀系数: $11 \times 10^{-6} \text{K}^{-1}$ |

应用特点:

- 1、PTFE、纤维的混合物在运动时可形成很好的转移膜保护对磨轴。
- 2、因其不含铅, 故对于人体无害。铜和钢板具有良好的导热性能, 表面的电镀层具有较好的耐腐蚀性。
- 3、已广泛运用于食品机械、医疗机械、烟草机械、饮料机械及其他绿色机械上。随着国际环保的逐步发展, SF-1W 将是 SF-1 产品的替代品。

SF-1B 青铜基材料




材料组织结构:

- | | |
|---------------------------|--|
| 1、聚四氟乙烯与铅的混合物 0.01~0.03mm | ■ 摩擦系数: 0.04~0.18 |
| 2、球形青铜粉: 0.2~0.3mm | ■ 导热系数: 18W/MK |
| 3、钢背: 0.5~3.3mm | ■ 使用温度范围: -195℃ ~300℃ |
| | ■ 线膨胀系数: $21 \times 10^{-6} \text{K}^{-1}$ |

应用特点:

- 1、PTFE、铅的混合物在运动时可形成很好的转移膜保护对磨轴。
- 2、烧结层和铜基板具有良好的导热性, 可迅速转移运作过程中产生的热量。
- 3、铜具有自润滑性能, 可运用于长期运作而无法停机检修的部位。
- 4、基体铜具有良好的抗腐蚀能力, 可运用于弱酸、强碱场合。
- 5、已广泛运用于冶金钢铁工业、高温炉钢环部位、水泥灌浆泵、螺旋式输送机、港口机械及船舶机械上等。
- 6、可在外部组合钢套, 或制成翻边, 达到内孔、端面同时使用的效果。

SF-1D 液压专用材料




材料组织结构:

- | | |
|-----------------------------------|--|
| 1、聚四氟乙烯与亲油性纤维混合物 0.01~0.03mm | ■ 摩擦系数: 0.04~0.18 |
| 2、球形青铜粉: 0.2~0.3mm | ■ 导热系数: 16W/MK |
| 3、钢背: 0.5~3.3mm | ■ 使用温度范围: -195℃ ~270℃ |
| 4、电镀层: 镀锡层厚 0.005mm 或镀铜层厚 0.008mm | ■ 线膨胀系数: $15 \times 10^{-6} \text{K}^{-1}$ |

应用特点:

- 1、PTFE、亲油性纤维的混合物在运动时可形成很好的转移膜保护对磨轴。
- 2、抗冲击能力强, 耐磨性能好, 摩擦系数低, 走合性能好, 无咬轴现象。
- 3、可用于旋转、摇摆、往复运动之中。
- 4、由于不含铅, 故可用于食品机械、医疗机械等绿色环保设备。
- 5、除具有 SF-1P 的特点小, 特别适合于往复运动频繁、大侧向力的场合, 适用于液压马达、汽车、摩托车减震器及各类液压油缸等领域。

SF-1S 不锈钢耐蚀材料



材料组织结构:


- 1、聚四氟乙烯与亲油性纤维混合物 0.01~0.03mm
- 2、球形青铜粉 :0.2~0.3mm
- 3、钢背: 0.5~3.3mm

- 摩擦系数: 0.04~0.20
- 导热系数: 16W/MK
- 使用温度范围: -195℃ ~270℃
- 线膨胀系数: $15 \times 10^{-6} \text{K}^{-1}$

应用特点:

- 1、PTFE、亲油性纤维的混合物在运动时可形成很好的转移膜保护对磨轴。
- 2、耐磨性能好, 摩擦系数低, 走合性能好, 无咬轴现象。
- 3、可用于旋转、摇摆、往复运动之中。
- 4、耐腐蚀性能好。
- 5、由于不含铅, 故适用于食品饮料机械、医疗机械等绿色环保设备。
- 6、典型用途: 主要运用于中酸、强碱场合、例如: 化工中酸碱流量计、泵、阀、印染机械、海洋工业耐腐蚀滑动部位。

JF-800 双金属材料



材料组织结构:


- 1、合金层: CuPb10Sn10
- 2、钢背: 0.6~5mm

- 合金层材质: CuPb10Sn10
- 摩擦系数: ≤ 0.12
- 最高使用温度: 260℃
- 合金层硬度: (60~90) HB

应用特点:

- 1、双金属合金材料中承载能力最强的一种。
- 2、适用于低速高载场合。
- 3、可在摩擦面加工各种油槽、油穴及油孔, 满足不同工况条件的需要。
- 4、产品性能稳定, 已通过“蓝宝石实验”, 疲劳强度达 125MPa 以上。
- 5、广泛运用于重型车的平衡桥衬套、垫片; 推土机的重动轮、支动轮、汽车钢板衬套等。

JF-850 双金属材料



材料组织结构:

- 1、合金层: CuSn6Zn6Pb3
- 2、钢背: 0.6~5mm

- 合金层材质: CuSn6Zn6Pb3
- 摩擦系数: ≤ 0.13
- 最高使用温度: 170℃
- 合金层硬度: (40~80) HB

应用特点:

- 1、双金属合金材料中承载能力较强的一种。
- 2、适用于低速高载场合。
- 3、可在摩擦面加工各种油槽、油穴及油孔。
- 4、广泛运用于汽车发动机、底盘、摩托车离合器、齿轮摩擦板和起重设备领域。

JF-930 双金属材料



材料组织结构:

- 1、合金层: CuSn6.5P0.1
- 2、钢背: 0.6~5mm

- 合金层材质: CuSn6.5P0.1
- 摩擦系数: ≤ 0.13
- 最高使用温度: 260℃
- 合金层硬度: (60~90) HB

应用特点:

- 1、结合强度高, 承载能力大, 耐磨性能好。
- 2、适用于低速高载场合。
- 3、可在摩擦面加工各种油槽、油穴及油孔。
- 4、具有无铅特点, 可以是其他有铅产品的替代产品。
- 5、广泛运用于矿山机械、汽机车、建筑机械、农用机械、轧钢机械等。



SF-2X 边界润滑材料



材料组织结构:

- 1、聚四氟乙烯与铅混合物 0.3~0.5mm
- 2、球形青铜粉: 0.2~0.3mm
- 3、钢背: 0.4~2.7mm
- 4、电镀层: 镀铜层 0.008mm

- 摩擦系数: 0.05~0.25
- 导热系数: 13W/MK
- 使用温度范围: -40℃ ~130℃
- 线膨胀系数: 11*10-6K-1

应用特点:

- 1、承载好, 耐磨性能好。
- 2、适用于高载低速下的旋转运动, 摇摆运动及经常在载荷下启闭频繁而不易形成流体动力润滑的场合。
- 3、表面的塑料层在加工成型时可留一定的余量, 装配压入座孔后可自行加工, 以达到更好的装配尺寸。
- 4、主要运用于汽车底盘、冶金机械、矿山机械、水利机械、建筑机械、农用机械、轧钢设备等。



SF-2Y 边界润滑材料



材料组织结构:

- 1、缩醛树脂与亲油性纤维混合物 0.3~0.5mm
- 2、球形青铜粉: 0.2~0.3mm
- 3、钢背: 0.4~2.7mm
- 4、电镀层: 镀锡层厚 0.005mm 或镀铜层厚 0.008mm

- 摩擦系数: 0.05~0.25
- 导热系数: 13W/MK
- 使用温度范围: -40℃ ~130℃
- 线膨胀系数: 11*10-6K-1

应用特点:

- 1、承载好, 耐磨性能好。
- 2、适用于高载低速下的旋转运动, 摇摆运动及经常在载荷下启闭频繁而不易形成流体动力润滑的场合。
- 3、表面的塑料层在加工成型时可留一定的余量, 装配压入座孔后可自行加工, 以达到更好的装配尺寸。
- 4、主要运用于进口纺织设备、柱塞泵摆动部位、汽车操纵杆部位等。
- 5、因其不含铅, 故可广泛运用于无铅领域。



SF-2S 边界润滑材料



材料组织结构:

- | | |
|-----------------------------------|----------------------|
| 1、缩醛树脂与亲油性纤维混合物 0.3~0.5mm | ■ 摩擦系数: 0.05~0.20 |
| 2、球形青铜粉: 0.2~0.3mm | ■ 导热系数: 13W/MK |
| 3、钢背: 0.4~2.7mm | ■ 使用温度范围: -40℃ ~130℃ |
| 4、电镀层: 镀锡层厚 0.005mm 或镀铜层厚 0.008mm | ■ 线膨胀系数: 11*10-6K-1 |

应用特点:

- 1、承载好, 耐磨性能好。
- 2、适用于干摩擦和少油润滑的场合。
- 3、目前产品已应用在摇摆运动、易磨损、易腐蚀的场合, 如卷扬机、推土机、印染机、采煤机及吊车、行车高空作业机等场合。



FB090 无油润滑材料



FB090 无油润滑材料是采用高密度铜合金带材为基体, 表面轧制菱形或半球形油穴。具有密度高、承载能力大、耐磨性能好、使用寿命长等优点, 该材料已广泛应用于起重机械、建筑机械、汽车拖拉机底盘、机床工业及采矿机械中, 还可以制成轴瓦、翻边轴套、止推垫片和球碗等。

- 基体材质: CuSn8P0.3 或 CuSn6.5P0.1
- 硬度: HB110~140
- 使用温度范围: -80℃ ~200℃
- 摩擦系数: ≤ 0.15
- 磨损量: ≤ 0.008

FB092 无油润滑材料



FB092 无油润滑材料是以青铜材料为基体。具有耐磨性能好, 使用寿命长等优点, 该产品在卷制成轴承前, 应布置 $\phi 4\text{mm} \sim \phi 6\text{mm}$ 的油孔, 面积达到 25%, 使油脂润滑充足。目前该产品已应用于输送机、升降机、卷扬机、校平机等中载、低速的场合。

- 基体材质: CuSn8P0.3 或 CuSn6.5P0.1
- 硬度: HB90~120
- 使用温度范围: -100℃ ~200℃
- 摩擦系数: ≤ 0.12
- 磨损量: ≤ 0.008

FB09G 青铜固体润滑材料



FB09G 青铜固体润滑材料是以青铜材料为基体，表面埋入固体润滑剂制作而成。由于此材料是以延伸率较高的铜合金材料为基体，所以可以制作特薄的卷制轴套，再加上理想的填充材料为耐磨剂，因此适用于汽车传动轴内作为耐磨的轴套使用，也可在无油润滑的场合使用。

- 基体材质: CuSn10P10+ 石墨
- 硬度: HB80~110
- 使用温度范围: -100℃ ~260℃
- 摩擦系数: ≤ 0.12
- 磨损量: ≤ 0.008

FB08G 固体润滑材料



FB08G 固体润滑材料是以 JF-800 双金属材料为基体，合金层埋入特殊固体润滑剂制作而成的新颖薄壁固体润滑材料。由于高强度承载的合金材料作基体，理想的填充材料为耐磨剂，合理的菱形块状润滑设计，使润滑面积达 25% 以上，因此，能发挥良好的润滑性和抗磨损性能。该材料主要应用于汽车变速齿轮箱、发电机、升降机、起重机及冶金机械行业。

- 基体材质: CuSn10P10+ 石墨
- 硬度: HB60~90
- 使用温度范围: -100℃ ~260℃
- 摩擦系数: ≤ 0.15
- 磨损量: ≤ 0.01

FR 四氟软带材料



FR 四氟软带材料是以青铜丝网为基体，通过特殊烧结工艺，表面轧制聚四氟乙烯（PTFE）和其他填充减摩材料的混合物。它具有较低的摩擦系数，较好的耐磨特性。由于它的柔软性能好，所以可作为钢与钢对磨的隔离膜，实现无间隙、无噪音、无油润滑、无需保养、无污染的理想目的。目前该材料广泛用于纺织机械、关节轴承、汽车门铰链等场合。

- 使用温度范围: -40℃ ~280℃
- 摩擦系数: 0.05~0.20

SF-2S 边界润滑材料



材料组织结构:

- | | |
|-----------------------------------|----------------------|
| 1、缩醛树脂与亲油性纤维混合物 0.3~0.5mm | ■ 摩擦系数: 0.05~0.20 |
| 2、球形青铜粉: 0.2~0.3mm | ■ 导热系数: 13W/MK |
| 3、钢背: 0.4~2.7mm | ■ 使用温度范围: -40℃ ~130℃ |
| 4、电镀层: 镀锡层厚 0.005mm 或镀铜层厚 0.008mm | ■ 线膨胀系数: 11*10-6K-1 |

应用特点:

- 1、承载好, 耐磨性能好。
- 2、适用于干摩擦和少油润滑的场合。
- 3、目前产品已应用在摇摆运动、易磨损、易腐蚀的场合, 如卷扬机、推土机、印染机、采煤机及吊车、行车高空作业机等场合。



FB090 无油润滑材料



FB090 无油润滑材料是采用高密度铜合金带材为基体, 表面轧制菱形或半球形油穴。具有密度高、承载能力大、耐磨性能好、使用寿命长等优点, 该材料已广泛应用于起重机械、建筑机械、汽车拖拉机底盘、机床工业及采矿机械中, 还可以制成轴瓦、翻边轴套、止推垫片和球碗等。

- 基体材质: CuSn8P0.3 或 CuSn6.5P0.1
- 硬度: HB110~140
- 使用温度范围: -80℃ ~200℃
- 摩擦系数: ≤ 0.15
- 磨损量: ≤ 0.008

FB092 无油润滑材料



FB092 无油润滑材料是以青铜材料为基体。具有耐磨性能好, 使用寿命长等优点, 该产品在卷制成轴承前, 应布置 $\phi 4\text{mm} \sim \phi 6\text{mm}$ 的油孔, 面积达到 25%, 使油脂润滑充足。目前该产品已应用于输送机、升降机、卷扬机、校平等中载、低速的场合。

- 基体材质: CuSn8P0.3 或 CuSn6.5P0.1
- 硬度: HB90~120
- 使用温度范围: -100℃ ~200℃
- 摩擦系数: ≤ 0.12
- 磨损量: ≤ 0.008

轴承的选择与计算

轴承的选型 Bearing Selection

杰盛无油轴承根据不同的工况条件设计了不少的轴承材料。用户在使用和设计时应当根据轴承的使用温度、轴承的承载面压、线速度、耐磨性能要求、运动类型、安装情况、轴承成本等各方面因素综合考虑。

SF bush have developed kinds of bearing material according to difference work condition, the user can select the material base on bearing work environment, load, speed, wear, resistance request, moving method, installation, the cost of the material etc.

面压计算 Bearing Load

直套、翻边轴承 Cylindrical bushes, flange bushes

$$P = \frac{F}{dL} \quad (\text{N/mm}^2)$$


F = 轴承载值 Load (N)
d = 轴径 Shaft (mm)
L = 轴承长度 Bearing Length (mm)

止推垫片 Thrust Washer

$$P = \frac{4F}{(D^2 - d^2)\pi} \quad (\text{N/mm}^2)$$

F = 垫片承载值 Load (N)
d = 垫片外径 Washer OD (mm)
L = 垫片内径 Washer ID (mm)

由于受配合间隙、材料强度、轴承倒角、内部油槽等原因的影响，轴承的真正承载面压 (P_{act}) 会大于理论计算值 (P_{mean})。
As the factor of clearance, bushes chamfer, oil groove etc. The actually load (P_{act}) is higher than theory of calculation (P_{mean}).



线速度计算 Velocity

旋转运动 Rotating motion

$$V = \frac{dn\pi}{1000 \times 60} \quad (\text{m/s})$$

D = 轴径 Shaft (mm)
n = 转速/分 Rpm

摇摆运动 Oscillating motion

$$V = \frac{Dc\theta\pi}{1000 \times 360 \times 60} \quad (\text{m/s})$$

d = 轴径 Shaft (mm)
c = 摇摆频率 Frequency (次数/分) θ
= 摇摆角度 Oscillating angle

往复运动 Reciprocating motion

$$V = \frac{2sc}{60} \quad (\text{m/s})$$

s = 行程长度 (mm)
c = 往复频率 Frequency (次数/分)

PV 值计算 $PV = PXV \quad (\text{N/mm}^2 \times \text{m/s})$

PV 是指轴承在一定的承载和线速度条件下的乘积之和。设备的 PV 值与轴承的使用寿命成反比关系，因此建议设计时设备的 PV 取值尽量使用比较低的安全 PV 值，以确保轴承会有更长的使用寿命。同时也要考虑设备上轴承实际的承载、线速度、使用温度等不能超过所选择材料的极限值，并尽可能地小。

PV is the product of the specific bearing load P and the sliding speed V which is very important design data. We recommend design lower PV value will lead to longer service life. Also don't exceed the max. Of material load, speed, temp. And lower if possible.

滑动轴承与座孔的装配 The Installation of The Sliding Bushing And The Housing

◎SF 系列轴承在装配前宜先用煤油或柴油清洗干净，然后在机油内浸油、沥干。轴承与座孔装配时，即要保证轴承在座孔中不发生转动和轴向移动，要使轴承外表面与座孔充分接触，一般应保证接触面积大于 70% 以上，以利于承受载荷和传导摩擦热，SF 系列轴承内表面是自润滑塑料，外表面是铜背，钢对钢的摩擦系数比钢对塑料的摩擦系数大，因此采用较轻盈配合，既保证使用时衬套不会在座孔内发生相对移动，又不会使衬套外径过大致使衬套内孔变形较大。

◎对于工作压力较高的场合为避免轴套走外圆，推荐用以下二方法：

1、加大轴套外径尺寸，内孔变形用较正棒校正。

2、安装时，座孔涂 ZY801 厌氧胶，增强轴套与座孔的结合强度。

◎对于外 < 55mm 的轴承可按图 A 所示，利用一个带有手柄的压头轴芯，小心操作，轻轻压力座孔中。

◎当轴承外径 > 55mm 时可按图 B 所示，利用带台肩的手柄以及一个“O”形圈和一个辅助圈小心操作，将轴承压入座孔中。

◎The Installation of SF Bush

◎SF bushes should be cleaned in kerosene or diesel oil first, immersed in engine oil and then dried up. When the bush is installed into housing, make sure the bush not rotating in the housing or moving in the axial direction and at the same time make the outer surface surface fully contact to the base hole, generally

guarantee the contact area over 70%, thus to improve load capacity and transmission of friction heat. The inner surface of SF bush is made of self-lubricating plastic, the outer surface steel backing, The friction coefficient of steel to steel is bigger than that of steel to plastic, So we should choose the light-graded tight fit, preventing the axle sleeve from moving in the base when working, and also preventing the inner holes from getting deformed and too big because of the large tight fit of the outer diameter.


◎Out circle of the axle sleeve should be avoided in the high-pressure working conditions. Two methods are recommended here:

1. Increase the outer diameter of the axle sleeve, and the deformation of inner holes can be calibrated with calibrating core stick.

2. When installing, apply ZY 801 Oxygen-hatred glue in the housing to streng then the combination strength between the axle sleeve and base hole.

◎For bush (outer diameter < 55mm), press the bush into the housing gently and carefully using an core axle with a handle. Fig A.

◎For bush (outer diameter > 55mm), press the bush into the housing gently and carefully using a handle with a shoulder, an “O” ring and an assisting circle. Fig B.




(图A a)平面式安装
(Fig A a)Plane Installation

- 1、压入芯轴
- 2、轴承座孔倒角 $0.8 \times 15^\circ$
- 3、轴承座
- 4、JS-F 轴承
- 5、嵌入肩直径
- R、芯轴端圆角半径

(b)嵌入式安装
(B)Inset Installation

- 1、Press the core axle into bushing
- 2、Housing chamfer at end: $0.8 \times 15^\circ$
- 3、Housing
- 4、JS-F bush
- 5、Diameter of inset shoulder
- R、Radius of the round angle of the core axle end




d2	dH
>55到100	d2 +0.25 d2 +0.25
>100到200	d2 +0.40 d2 +0.35
>200到300	d2 +0.50 d2 +0.40



**JINTAI
BEARING**

SENDOO DESIGN
13957330053 滑动平面设计



RAPIDBBS.CN



湖南锦泰五金机电有限公司

Hunan Jintai Hardware and Machinery Co., LTD

地址:中国湖南省长沙市芙蓉区锦泰广场

湖南国际商务中心 503

电话: 86-731-84770165

传真: 86-731-84770163

官网: <http://www.slide-bearing.com>

邮箱: sales@slide-bearing.com

Add: No.503,HunanInternational Commerce Center,
Jintai Square,Changsha,410001,Hunan,China.

Tel: 86-731-84770165

Fax: 86-731-84770163

Website:<http://www.slide-bearing.com>

E-mail: sales@slide-bearing.com